



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁴ : A61K 47/00, 9/22	A1	(11) International Publication Number: WO 89/ 09066 (43) International Publication Date: 5 October 1989 (05.10.89)
(21) International Application Number: PCT/DK89/00068 (22) International Filing Date: 22 March 1989 (22.03.89) (31) Priority Application Numbers: PCT/DK88/00049 6062/88 (32) Priority Dates: 24 March 1988 (24.03.88) 31 October 1988 (31.10.88) (33) Priority Country: DK (71) Applicant (for all designated States except US): BUKH MEDITEC A/S [DK/DK]; Strandvejen 122, DK-2900 Hellerup (DK). (72) Inventors; and (75) Inventors/Applicants (for US only) : BAR-SHALOM, Daniel [IL/DK]; Rypevænget 213, DK-2980 Kokked- al (DK). KINDT-LARSEN, Ture [DK/DK]; Hotel- stien 8, DK-2950 Vedbæk (DK).		(74) Agent: PLOUGMANN & VINGTOFT; Sankt Annæ Plads 11, DK-1250 Copenhagen K (DK). (81) Designated States: AT, AT (European patent), AU, BB, BE (European patent), BF (OAPI patent), BG, BJ (OAPI patent), BR, CF (OAPI patent), CG (OAPI pa- tent), CH, CH (European patent), CM (OAPI patent), DE, DE (European patent), DK, FI, FR (European patent), GA (OAPI patent), GB, GB (European pa- tent), HU, IT (European patent), JP, KP, KR, LK, LU, LU (European patent), MC, MG, ML (OAPI pa- tent), MR (OAPI patent), MW, NL, NL (European patent), NO, RO, SD, SE, SE (European patent), SN (OAPI patent), SU, TD (OAPI patent), TG (OAPI pa- tent), US. Published <i>With international search report.</i> <i>With amended claims.</i>
(54) Title: CONTROLLED RELEASE COMPOSITION		
(57) Abstract <p>A composition for controlled delivery of an active substance into an aqueous phase by erosion at a substantially constant rate of a surface or surfaces of the composition, the composition comprising a matrix of at least one substantially water soluble crystalline polymer, one or more surface active agents dispersed in the crystalline polymer phase, at least one active substance substantially homogeneously dispersed in the crystalline polymer phase and/or located in geometrically well-defined zones within the crystalline polymer phase and/or dispersed in the surface active agent and, optionally, a filler. The surface active agent and/or the active substance substantially eliminates water diffusion in the interface between the polymer crystals. In an alternative embodiment, the composition comprises a matrix of room-temperature vulcanizing rubber (RTV rubber) in which particles of a superabsorbent polymer are substantially homogeneously distributed and at least one active substance substantially homogeneously dispersed in the matrix and/or located in geometrically well-defined zones within the matrix.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FR	France	ML	Mali
AU	Australia	GA	Gabon	MR	Mauritania
BB	Barbados	GB	United Kingdom	MW	Malawi
BE	Belgium	HU	Hungary	NL	Netherlands
BG	Bulgaria	IT	Italy	NO	Norway
BJ	Benin	JP	Japan	RO	Romania
BR	Brazil	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	LI	Liechtenstein	SN	Senegal
CH	Switzerland	LK	Sri Lanka	SU	Soviet Union
CM	Cameroon	LU	Luxembourg	TD	Chad
DE	Germany, Federal Republic of	MC	Monaco	TG	Togo
DK	Denmark	MG	Madagascar	US	United States of America
FI	Finland				

CONTROLLED RELEASE COMPOSITION

FIELD OF INVENTION

The present invention relates to a composition for controlled delivery of an active substance into an aqueous phase.

5 BACKGROUND OF THE INVENTION

It is known to obtain sustained release of an active substance, e.g. a pharmaceutically active powder, by embedding it in a matrix of an insoluble substance from which the active substance will gradually diffuse. Sustained release of an active substance contained in a
10 tablet core may also be achieved by applying to the core a semi-permeable coating through which water and dissolved active substance may diffuse or an insoluble coating provided with a hole through which the active substance is released. Gradual release of an active substance may furthermore be obtained by microencapsulating particles
15 of an active substance in one or more layers of film which may be of different types, e.g. of a type which mediates diffusion of the active substance or release thereof in the intestines.

These conventional ways of providing sustained release of an active substance have certain drawbacks, in that it is difficult to maintain
20 a constant concentration of the active substance, for example a constant concentration of a pharmaceutically active substance in plasma for the entire period when the dosage form is present in the body. In particular, this may be the problem with drugs which have a brief half-life in the body. Furthermore, the penetration of water
25 through diffusion coatings may cause hydrolysis of active substances which are unstable in an aqueous environment.

The purpose of the present invention is to overcome these drawbacks by providing a composition from which release of an active substance is strictly controlled and which prevents degradation of the active
30 substance by hydrolysis until the time of release.

SUMMARY OF THE INVENTION

Accordingly, in one embodiment, the present invention relates to a composition for controlled delivery of an active substance into an aqueous phase by erosion at a substantially constant rate of a surface or surfaces of the composition, the composition comprising

a matrix of a substantially water soluble crystalline polymer or a mixture of substantially water soluble crystalline polymers,

a surface active agent or a mixture of surface active agents dispersed in the crystalline polymer phase in an amount of 0-50% by weight of the crystalline polymer and surface active agent, the surface active agent comprising a compound or compounds having at least one domain which is compatible with the crystalline polymer phase and at least one other domain which is substantially lipophilic, and having a melting point which is lower than that of the crystalline polymer,

at least one active substance substantially homogeneously dispersed in the crystalline polymer phase and/or dispersed in the surface active agent and/or located in geometrically well-defined zones within the composition, and

optionally, a filler,

the surface active agent and/or the active substance reducing the water affinity of domains between grains and in cracks in the crystalline polymer matrix and in the crystalline polymer matrix itself, thereby substantially eliminating water diffusion in the interface between the polymer crystals, so that the erosion is predominantly effected by the dissolving action of an aqueous medium on a surface or surfaces of the composition exposed to the medium.

The combination of the matrix and the active substance and/or the surface active agent must be substantially impenetrable to fluids of the aqueous phase, for example body fluids present where the composi-

tion of the invention is introduced into the body (e.g. in the gastrointestinal tract, including the rectum, in the vagina or subcutaneously) or into a body cavity via a catheter (e.g. the urinary bladder, the gall bladder, the uterus, a central nervous system cavity, infectious/malignant/post-operative cavities, etc.), in order to avoid degradation of the active substance residing in the matrix due to the action of water in the case of an active substance which is susceptible to hydrolysis. The inclusion of the active substance in a matrix into which water diffusion is substantially eliminated will thus impart stability to the composition, so that the active substance will remain active even when the composition has been exposed to body fluids or other fluids for the predetermined time. As the fluids can only act on the surface of a matrix of this type, the active substance embedded therein is only exposed to the fluids in question when it is released or immediately prior to its release from the matrix. A matrix of a type which is substantially impenetrable to water will therefore ensure the stability of the active substance in the matrix for the entire period of time when the composition is present in the aqueous phase, for example a body cavity, until the time when the active substance is released, and will also ensure a controlled and reproducible release rate of the active substance from the matrix, since the release proceeds gradually from the surface or surfaces of the matrix exposed to the fluids in question.

The rate at which the active substance is released from the matrix is a predetermined rate, i.e. a rate which is controllable over a certain period of time. The release rate required in each particular instance may *inter alia* depend on the amount of active substance to be released for it to exert the desired effect, as well as on the overall dosage of the active substance contained in the matrix. The substance of which the matrix is composed and the distribution of the active substance in the matrix may therefore be selected according to one or more of these criteria to ensure the desired level of release of the active substance.

The composition of the invention has the advantage that the dosage of the active substance included in the matrix may be measured so that an appropriate constant or pulsatile dosage thereof will be available

in the aqueous phase for the entire period of time that the composition is present in the aqueous phase; the nature of the matrix structure, i.e. its water-impenetrability, prevents degradation by hydrolysis or other means of the active substance due to diffusion of water into the matrix even if the active substance in itself is unstable in an aqueous environment.

Due to the controlled release of the active substance obtainable from the composition of the invention, it is possible to obtain a substantially constant rate of release or a controlled pulsatile release of the active substance over a specific period of time, corresponding to the dosage necessary for the treatment in question, so that adherence to a strict dosage regimen, e.g. requiring administration of a drug at set intervals up to several times a day, may be dispensed with. Furthermore, it is possible to include two or more different active substances in the composition of the invention, adapted to be released at different concentrations and/or intervals, thus making it easier for patients to follow a prescribed regimen.

An additional advantage of the composition of the invention, compared to other known controlled release compositions, is that it may be produced by relatively simple and inexpensive methods, e.g. by extrusion, as will be explained in more detail below. Furthermore, the composition according to the invention allows for the incorporation of high concentrations of the active substance relative to the composition's size. This is obviously a great advantage, notably when the composition is to be used for the delivery of a pharmaceutically active substance, since it allows for the delivery of the required amount of the active substance without the composition being unnecessarily large. In addition, sparingly soluble or non-soluble active substances may be readily incorporated into the composition of the invention, since such substances are compatible with the lipophilic domains of the surface active agent. The composition of the invention may thus be used for the delivery of, for example, sparingly soluble or non-soluble pharmaceutical powders which can otherwise be difficult to administer.

Rather than comprising a water soluble crystalline polymer or mixture of such polymers, the matrix may comprise a substance which is non-soluble in water, together with the active substance and a hydrophilic substance which is at least partly accessible to the fluids of the aqueous phase and which swells in the presence of said fluids, resulting in a localized disruption of the matrix in the vicinity of the hydrophilic substance and the release of the active substance.

The invention, in another embodiment, thus relates to a composition for controlled delivery of an active substance into an aqueous phase, the composition comprising

a matrix of room-temperature vulcanizing rubber (RTV rubber) in which particles of a superabsorbent polymer are substantially homogeneously distributed, the superabsorbent polymer particles also being present substantially near the surface of the composition, and

at least one active substance substantially homogeneously dispersed in the matrix and/or located in geometrically well-defined zones within the matrix,

in which the liquid of the aqueous phase is able to diffuse into the surface of the matrix at a limited rate, resulting in swelling of the superabsorbent polymer particles and the localized disruption of the matrix in the vicinity of the swollen particles, whereby the active substance is released in a specifically controlled manner according to its distribution in the matrix.

DETAILED DISCLOSURE OF THE INVENTION

In the first embodiment of the invention, i.e. when matrix of the composition comprises a substantially water soluble crystalline polymer or a mixture of substantially water soluble crystalline polymers, a surface active agent will typically be dispersed in the crystalline polymer phase.

The surface active agent comprises a compound or compounds having at least one domain which is compatible with the crystalline polymer phase and at least one other domain which is substantially lipophilic. The term "compatible", as used in the context of the invention, refers to the fact that the surface active agent is able to become emulsified in the melted polymer, as explained below. The surface active agent functions partly as a repair medium, in that it has a substantially hydrophilic domain which gives it affinity to the crystalline polymer phase, thereby filling in domains between grains and in cracks in the crystalline polymer matrix, and partly as a surfactant, in that the substantially lipophilic domains reduce the water affinity in the interfaces between the grains and in the cracks in the crystal structure, thereby substantially eliminating water diffusion in the interface between the polymer crystals.

The above-mentioned cracks and grains in the crystalline polymere matrix are a result of the process in which the crystals are formed. During the crystallization process the matrix shrinks and tends to form cracks and imperfect zones between the crystal grains. In order to retain its function as a repair medium, the surface active agent should be mobile after the polymer material of the matrix has solidified and the crystals have been formed. Therefore, the melting point of the surface active agent must be lower than that of the crystalline polymer phase.

In order for the surface active agent to function properly as a repair medium for the cracks and grains in the matrix, it is further necessary that a substantially homogenous distribution of the surface active agent can be obtained in the melted polymer prior to crystallization. Thus, the surface active agent must be capable of becoming emulsified in the melted polymer.

It has been found that substantially hydrophobic active substances tend to result in a decrease in the erosion rate of the composition. Substantially hydrophilic or water-soluble active substances have been shown to have the opposite effect, i.e. they tend to result in a faster erosion of the matrix. It has furthermore been found that if

the composition is prepared without an active substance, the composition will tend to erode at a relatively fast rate.

The degree of dispersion of the surface active agent in the matrix seems to be important for the erosion rate of the matrix, a more uniform dispersion resulting in a slower erosion rate. It is thus
5 believed that substantially hydrophobic active substances tend to lead to a more uniform dispersion of the surface active agent, thereby leading to a decreased erosion rate of the matrix, while non-hydrophobic active substances have the opposite effect.

10 When the composition is prepared with an active substance which is not substantially hydrophobic, or when the content of the active substance in the composition is relatively low, it may therefore be desirable to add one or more fillers in order to modify the disper-
15 sion of the surface active agent and reduce the erosion rate of the matrix. It is believed that the addition of a filler serves to increase the viscosity of the mixture, whereby the surface active agent becomes more uniformly dispersed in the matrix. Examples of suitable fillers are dextrin, sucralfate, calcium hydroxyl-apatite, calcium phosphate and fatty acid salts such as magnesium stearate. The filler
20 may be added in an amount so that the combination of the filler and the active substance comprises up to about 60%, typically up to about 50%, by weight of the composition.

The surface active agent is typically a non-ionic emulsifier comprising one or more fatty acid esters and/or fatty acid ethers, for
25 example a fatty acid ester and/or fatty acid ether having carbon chains of from 12 to 24 carbon atoms, typically from 12 to 20 carbon atoms, such as an ester and/or ether of palmitic acid or stearic acid. Typical surface active agents may comprise a polyglycol ester or ether, a polyethylene glycol ester or ether, a polyhydroxy ester
30 or ether and/or a sugar ester or ether such as a sorbitan ester or ether. The surface active agent will suitably have an HLB (hydrophilic-lipophilic balance) value of from about 4 to about 16. Furthermore, the surface active agent is preferably an emulsifier which is approved for use in products to be ingested by humans or animals,
35 i.e. pharmaceuticals and/or foodstuffs. A preferred surface active

agent is polyethylene glycol monostearate, in particular polyethylene glycol 400 monostearate. Tartaric acid, citric acid and lactic acid esters of mono- and diglycerides, as well as fatty acid esters of glycerol, may also be employed as a surface active agent.

- 5 It may in certain cases be desirable to incorporate a mixture of surface active agents into the matrix, in order to improve the dispersion of the primary surface active agent in the matrix and reduce the erosion rate.

10 In some cases, the active substance itself will be capable of functioning as a surface active agent, i.e. it will have at least one domain which is compatible with the crystalline polymer phase and at least one other domain which is substantially lipophilic, so that the active substance alone will be capable of becoming substantially
15 homogeneously dispersed in the crystalline polymer phase and substantially eliminating diffusion of water into the matrix. In this case, the role of the surface active agent, i.e. its function as a repair medium and as a surfactant, will be partially or completely fulfilled by the active substance itself, and little or no surface active agent may be required. Thus, when the active substance itself
20 has properties of a non-ionic emulsifier, the surface active agent may be absent from the composition or may be present in the composition in an amount of, for example, about 0-2% by weight of the matrix.

When the active substance does not possess properties of a surface
25 active agent, the surface active agent is typically present in the composition in an amount of about 2-50%, e.g. about 5-50%, typically about 10-40%, more typically about 15-35%, such as about 20-30%, by weight of the crystalline polymer and surface active agent. As mentioned above, a surface active agent content of less than 2% may
30 however be employed when the active substance possesses surface active agent properties. On the other hand, a maximum surface active agent content of about 50%, depending on the nature of the surface active agent, the active substance and the crystalline polymer, as well as on the desired delivery characteristics of the composition,
35 will be sufficient to ensure the required repair and surfactant

effects. If the content of the surface active agent exceeds about 50%, there is a risk of phase inversion, whereby the surface active agent may become the continuous phase.

The crystalline polymer matrix typically comprises a polyglycol, e.g. in the form of a homopolymer and/or copolymer. Preferred polymers are polyethylene glycols or block copolymers of ethylene oxide and propylene oxide. Polyethylene glycols which are suitable for use in the crystalline polymer matrix are those having a molecular weight of from about 2000 to about 500,000 daltons, typically from about 5000 to about 100,000 daltons, more typically from about 10,000 to about 50,000 daltons, and especially from about 20,000 to about 35,000 daltons. A preferred polyethylene glycol is one which has a molecular weight of about 35,000 daltons. Typical block copolymers may be comprised of up to about 30% by weight of the polypropylene oxide based block, and have a molecular weight of above about 5000 daltons, typically about 5000 to about 30,000 daltons, more typically about 8000 to about 15,000 daltons.

The crystalline polymer matrix must have a melting point which is above the temperature of the aqueous medium in which the composition of the invention is to be used. Thus, the polymer(s) employed in the matrix will suitably have a melting point of about 20-120°C, typically about 30-100°C, more typically about 40-80°C, depending on the how the composition is to be employed. In particular, when the composition of the invention is used for the delivery of a drug for human or veterinary use, the matrix will suitably have a melting point of about 40-80°C.

The active substance to be delivered by the composition according to the invention can be a drug for human or veterinary use, a vitamin or other nutritional supplement, a disinfectant, a deodorant or another substance to be administered continuously in an aqueous environment.

The composition of the invention is especially suitable for the delivery of an active substance which is a pharmaceutically active substance, in particular a pharmaceutically active powder. The pharmaceutically active substance or substances included in the composi-

tion of the invention may be selected from many therapeutic categories, in particular from substances which may advantageously be administered orally, rectally, vaginally or subcutaneously, or administered to a body cavity (e.g. the urinary bladder, the gall bladder, the uterus, a central nervous system cavity, infectious/malignant/post-operative cavities, etc.). Examples of such substances are antimicrobial agents, analgesics, antiinflammatory agents, counterirritants, coagulation modifying agents, diuretics, sympathomimetics, anorexics, antacids and other gastrointestinal agents, antiparasitics, antidepressants, antihypertensives, anticholinergics, stimulants, anti-hormones, central and respiratory stimulants, drug antagonists, lipid-regulating agents, uricosurics, cardiac glycosides, electrolytes, ergot and derivatives thereof, expectorants, hypnotics and sedatives, antidiabetic agents, dopaminergic agents, antiemetics, muscle relaxants, para-sympathomimetics, anticonvulsants, antihistamines, β -blockers, purgatives, antiarrhythmics, contrast materials, radiopharmaceuticals, antiallergic agents, tranquilizers, vasodilators, antiviral agents, and antineoplastic or cytostatic agents or other agents with anticancer properties, or a combination thereof.

Other suitable active substances may be selected from contraceptives and vitamins as well as micro- and macronutrients.

The composition is in addition suitable for the delivery of polypeptides, for example hormones such as growth hormones, enzymes such as lipases, proteases, carbohydrases, amylases, lactoferrin, lactoperoxidases, lysozymes, nanoparticles, etc., and antibodies. The composition may also be employed for the delivery of microorganisms, either living, attenuated or dead, for example bacteria, e.g. gastrointestinal bacteria such as streptococci, e.g. *S. faecium*, *Bacillus* spp. such as *B. subtilis* and *B. licheniformis*, lactobacteria, *Aspergillus* spp., bifidogenic factors, or viruses such as indigenous viruses, enteroviruses, bacteriophages, e.g. as vaccines, and fungi such as baker's yeast, *Saccharomyces cerevisiae* and fungi imperfecti. The composition may also be used for the delivery of active agents in specialized carriers such as liposomes, cyclodextrines, nanoparticles, micelles and fats.

One of the uses for which the composition of the invention is well-suited is the delivery of antimicrobial agents to the vagina. Examples of such agents are antifungals, for example imidazole antifungals such as clotrimazole, econazol, ketoconazole and miconazole, 5 polyene antifungal antibiotics such as nystatin, and antiprotozoals such as metronidazole and ornidazole.

A pharmaceutically active powder to be administered by the composition of the invention will suitably have a particle size of from about 0.1 μm to about 500 μm , typically from about 0.5 μm to about 10 300 μm , more typically from about 1 μm to about 200 μm , especially from about 5 μm to about 100 μm .

The active substance will suitably be present in an amount of up to about 60%, typically up to about 50%, by weight of the composition. An active substance content of about 60% is contemplated to be the 15 maximum content which still allows for a sufficient content of the crystalline polymer matrix and the surface active agent in the composition. The active substance may, on the other hand, be present in the composition in much smaller amounts, depending on the nature and strength of the active substance in question.

20 As mentioned above, the presence of the surface active agent and/or the active substance in the crystalline polymer matrix will reduce the water affinity of domains between grains and in cracks in the matrix, thereby substantially eliminating water diffusion in the interface between the polymer crystals, so that the erosion is predominantly effected by the dissolving action of an aqueous medium on 25 a surface or surfaces of the composition exposed to the medium. Diffusion of water into the composition is thus substantially limited to the surface layer of the matrix, whereby the matrix is eroded at a substantially constant and pH-independent rate. As a result, a substantially zero order release of the active substance is obtained, 30 the term "zero order" referring to the fact that the release rate of the active substance is substantially constant with time, when the active substance is substantially homogeneously distributed in the matrix. In the case of the active substance being located in geometrically well-defined zones within the matrix, the result of the 35

constant erosion rate of the matrix will be a strictly controlled pulsatile release of the active ingredient.

The geometric form of the composition is important for the obtainment of the above-mentioned controlled zero order or pulsatile release.

- 5 Thus, in a preferred version of the invention, the composition of the invention has a geometric shape which enables a substantially constant surface area to become exposed during erosion of the matrix. The composition may thus have the shape of a cylindrical rod which is provided with a coating which is substantially insoluble in and
10 impermeable to fluids such as body fluids during the intended release period, the coating having an opening at one or both ends. Polymers useful as coatings are preferably those which are possible to process by extrusion, solution or in the form of a dispersion. Most preferred are those which are available in a food grade or pharmaceutical grade
15 quality. Examples of such polymers are cellulose acetate, polyamide, polyethylene, polyethylene terephthalate, polypropylene, polyurethane, polyvinyl acetate, polyvinyl chloride, silicone rubber, latex, polyhydroxybutyrate, polyhydroxyvalerate, teflon, polylactic acid or polyglycolic acid and copolymers thereof, copolymers such as ethylene
20 vinyl acetate (EVA), styrene-butadiene-styrene (SBS) and styrene-isoprene-styrene (SIS).

- The coating may further comprise any of the above-mentioned matrix materials in a form which erodes at a substantially slower rate than the rest of the matrix. The coating may thus comprise a matrix of
25 one or more substantially water soluble crystalline polymers and a surface active agent, the coating being one which is eroded in the aqueous phase at a substantially slower rate than the matrix material comprising the active substance, whereby a substantially constant area of the matrix comprising the active substance is exposed during erosion of the composition, and whereby the coating is
30 substantially eroded upon erosion of the matrix comprising the active substance. Such a coating will be designed so that its longitudinal erosion rate is substantially the same as the longitudinal erosion rate of the matrix, whereby the matrix and the coating will erode
35 longitudinally towards the center of the composition at substantially the same rate. Thus, when the matrix has been completely eroded by

the aqueous medium, the coating will also be substantially completely eroded. A composition having such a coating has the obvious advantage of being completely biodegraded upon release of the active substance. Such a coating will typically be a combination of a polyethylene glycol and a mixture of, for example, polyethylene glycol 400 monostearate and another surface active agent, and may also include a filler. The content of the mixture of surface active agents and the filler in the coating will be determined in each particular case according to the characteristics, e.g. erosion rate and size, of the matrix comprising the active substance.

In addition, the coating may be one which disintegrates or crumbles after erosion of the matrix. A coating of this type would remain intact as long as it was supported by the matrix containing the active substance, but it would lack the ability to remain intact after erosion of the matrix, whereby it would then disintegrate or crumble, so that it would not remain in e.g. a human or animal for any significant amount of time after the complete erosion of the matrix and the release of the active substance.

A composition having the shape of a cylindrical rod may also be prepared without a coating, in which case a substantially or nearly zero order release of the active substance may, for example, be obtained when the active substance is substantially located in the exterior of the composition.

Alternatively, the composition may have the shape of a hollow cylinder or a hollow hemisphere. The term "cylindrical rod" or "hollow cylinder", as used in the context of the present invention, is understood to comprise not only those geometrical forms having a substantially circular cross-section, but also other substantially cylindrical forms, e.g. those having a somewhat flattened cross-section, for example a substantially oval or ellipse shaped cross-section. In addition, other geometrical shapes which allow only a relatively small reduction in the composition's surface area, thereby providing a near zero order release of an active substance substantially homogeneously distributed in the composition, for example a tablet-shaped

or slab-shaped composition having a flattened and substantially rectangular or ellipse-shaped cross-section, may also be employed.

It will also be understood by a person skilled in the art that the specific finished form of the composition of the invention may comprise certain minor modifications in order to facilitate the use of the composition in question. For example, a cylindrical rod-shaped composition for delivery of a pharmaceutical powder may have rounded ends so as to avoid possible injury or discomfort when the composition is introduced into the body. In addition, the hollow interior of a composition having the shape of a hollow cylinder may optionally be filled with a readily soluble substance, such as low molecular weight polyethylene glycol, e.g. polyethylene glycol with a molecular weight of about 1500-6000.

As mentioned above, the active substance can be substantially homogeneously dispersed in the crystalline polymer matrix, in which case a substantially zero order release of the active substance is obtained. Alternatively, a pulsatile release of the active substance may be obtained in a composition of the invention which comprises alternating layers. A pulsatile release may thus be obtained with a composition having the above-mentioned shape of a cylindrical rod and comprising alternating substantially transverse layers of a layer comprising the crystalline polymer matrix and the surface active agent, and optionally comprising the active ingredient substantially homogeneously dispersed in the matrix, and a layer comprising the active ingredient, the active ingredient optionally being substantially homogeneously dispersed in the crystalline polymer and the surface active agent. Similarly, a composition in the form of a hollow cylinder may comprise alternating layers of a layer comprising the crystalline polymer matrix and the surface active agent, and optionally comprising the active ingredient substantially homogeneously dispersed in the matrix, and a layer comprising the active ingredient, the active ingredient optionally being substantially homogeneously dispersed in the crystalline polymer and the surface active agent. In a composition comprising alternating layers, the alternating layers may comprise, respectively, two or more different active substances.

These two release patterns (i.e. zero order and pulsatile) may also be combined so that a uniform release of one active substance (for example at a fairly low dosage level) alternates with the release in bursts of the same or another active substance (for example at a
5 higher dosage level).

In another embodiment of the invention, the controlled delivery of an active substance into an aqueous phase is obtained, as mentioned above, with a composition comprising a matrix of room-temperature vulcanizing rubber (RTV rubber) in which particles of a superabsor-
10 bent polymer are substantially homogeneously distributed, the superabsorbent polymer particles also being present substantially near the surface of the composition, so that the liquid of the aqueous phase is able to diffuse into the matrix at a limited rate, resulting in swelling of the superabsorbent polymer particles and the localized
15 disruption of the matrix in the vicinity of the swollen particles, whereby the active substance is released. Diffusion of water into the composition according to this embodiment of the invention is also substantially limited to the surface layer, whereby the active substance is released in a specifically controlled manner according to
20 its distribution in the matrix.

The employed RTV rubber typically comprises one or two component RTV silicon elastomers based on polydimethylsiloxane. The matrix of RTV rubber additionally comprises a catalyst and, optionally, a cross-linking agent. Suitable catalysts are stannous octoate or about 0.01-
25 0.1% of a platinum-divinyldisiloxane complex containing about 3-3.5% platinum. Suitable cross-linking agents are 0-40% of 1,3-divinyldisiloxane, 1,1,3,3-tetramethyldisiloxane or 1,3,5,7-tetramethylcyclotetrasiloxane.

The superabsorbent polymer particles are particles which are able to
30 remain in a semi-solid state upon absorption of water or other liquids, and which are able to absorb at least about 10 times their own weight in water, typically at least about 100 times their own weight in water, especially at least about 200 times their own weight in water. The superabsorbent polymer particles are also able to remain

in a semi-solid state upon absorption of bodily fluids, and are able to absorb at least about 5 times their own weight in bodily fluids, typically at least about 20 times their own weight in bodily fluids, especially at least about 40 times their own weight in bodily fluids.

- 5 Typical superabsorbent polymers which are suitable for use in this embodiment of the invention are polyacrylic acid, modified polyacrylic acid, carboxymethyl cellulose, modified carboxymethyl cellulose and cross-linked polyvinyl pyrrolidone.

- 10 The extent of the localized disruption will *inter alia* be determined by the desired rate of release of the active substance, but it should in any case be sufficient to make other superabsorbent polymer particles accessible to the fluids in question, so as to ensure a progressive disruption of the matrix from the surface inwards at a substantially uniform rate. The amount of superabsorbent polymer to
15 be included in the matrix varies according to the swelling power of the specific superabsorbent polymer selected and the way in which it is arranged in the matrix, but it is suitably present in an amount of about 5-75%, typically about 10-50%, more typically about 20-40% by weight of the matrix.

- 20 The active substance included in this embodiment of the invention may be any of the substances mentioned above, i.e. a drug for human or veterinary use, a vitamin or other nutritional supplement, a disinfectant, a deodorant or another substance to be administered continuously in an aqueous environment, and especially a pharmaceutically
25 active powder, e.g. of the type and particle size listed above. The active substance is present in an amount of up to about 60%, typically up to about 50%, by weight of the composition, but it may also be present in much smaller amounts.

- The composition according to this embodiment of the invention must
30 also have a geometric shape which enables a substantially constant surface area to become exposed during erosion of the matrix, whereby the desired zero order or pulsatile release of the active substance is obtained according to its distribution in the composition. The specific geometric shape can thus be any of those which are mentioned
35 above.

- The active substance in this embodiment of the invention may be substantially homogeneously dispersed in the matrix, in which case a substantially zero order release of the active substance will be obtained. The composition in this embodiment may also comprise alternating layers, in which case a pulsatile release of the active substance will be obtained. A pulsatile release may thus be obtained with a composition according to this embodiment of the invention having the above-described shape of a cylindrical rod and comprising alternating substantially transverse layers of a layer comprising the matrix, and optionally comprising the active ingredient substantially homogeneously dispersed in the matrix, and a layer comprising the active ingredient, the active ingredient optionally being substantially homogeneously distributed in matrix material. Similarly, a composition in the form of a hollow cylinder may comprise alternating longitudinal layers of a layer comprising the matrix, and optionally comprising the active ingredient substantially homogeneously dispersed in the matrix, and a layer comprising the active ingredient, the active ingredient optionally being substantially homogeneously distributed in matrix material.
- As explained above, the alternating layers may comprise, respectively, two or more different active substances. The two release patterns (i.e. zero order and pulsatile) may similarly also be combined in a composition according to this embodiment of the invention, so that a uniform release of one active substance (for example at a fairly low dosage level) alternates with the release in bursts of the same or another active substance (for example at a higher dosage level).

The composition according to either embodiment of the invention may furthermore be used in the preparation of a multiple units pharmaceutical formulation, e.g. in the form of a capsule or tablet. A multiple units pharmaceutical formulation is a formulation which comprises a multiplicity of individual units in such a form that the individual units will be made available upon disintegration of the formulation, typically a capsule or tablet, in the stomach of humans or animals ingesting said formulation. Thus, in this case, at least some of the individual units in said multiple units pharmaceutical formulation

will consist of the composition of the invention, the individual units being of a size which allows them to be incorporated into such a formulation.

The composition of the invention may be produced by various methods
5 which are either known *per se* in the pharmaceutical industry or which, for example, are used in the production of polymer-based materials, depending upon the desired embodiment and the materials employed in the composition in question. As mentioned above, one
10 advantage of the composition according to the invention is that it may be produced by methods which are relatively simple and inexpensive.

A composition without a coating may thus be produced by, for example, extrusion, injection molding or compression molding, while a composition with a coating may be produced by, for example, co-extrusion of
15 the coating with the matrix and the active substance, extrusion and dip coating, injection molding and dip coating, or by extrusion or injection molding and solvent coating by spraying or dipping.

For the preparation of a composition having a matrix of a crystalline polymer, the polymer and the surface active agent will typically be
20 mixed while heating at a temperature sufficient to melt the polymer, and while stirring, so as to obtain a substantially homogeneous mixture. In the case of the active substance being included in the matrix, it may either be added to the molten mixture of the polymer and the surface active agent or it may be added to the mixture prior
25 to heating. The molten mixture is then e.g. extruded or injected, as explained below. For the preparation of a composition for pulsatile release of the active substance, the active substance may conveniently be included in matrix material, the mixture of the active substance and the matrix material being e.g. extruded or injected in layers
30 which alternate with layers of the matrix without the active substance.

For the preparation of a composition having a matrix of RTV rubber, the components of the matrix, i.e. the RTV rubber material, the superabsorbent polymer, and the catalytic accelerator and/or cross-

linking agent, are typically mixed together at room temperature while stirring, after which the mixture is e.g. extruded or injected as explained below. The active substance may be added to the mixture prior to e.g. extrusion or injection or it may be e.g. extruded or
5 injected separately, according to the desired characteristics of the composition.

For example, for the production of a composition which has the shape of a cylindrical rod, the matrix material comprising the active substance may be injected into a pre-formed tube. Alternatively, a
10 cylindrical rod-shaped composition may be produced by injecting alternating layers comprising at least, respectively, the matrix material and the active substance into said tube. A cylindrical rod-shaped composition may also be produced by, for example, extruding the matrix material with the active substance dispersed therein,
15 followed by dip coating; or by co-extrusion of a) the matrix material with the active substance dispersed therein and b) the coating.

A cylindrical rod shaped composition may also be produced by injection molding, including two-component or multiple-component injection molding, of the coating and the matrix comprising the active substance. Injection molding is especially suitable for a composition
20 with an erodable coating or a coating which disintegrates or crumbles upon erosion of the matrix, but it is also applicable for other compositions. Typically, a cylinder which functions as a coating is produced in a first step around a core of e.g. iron, after which the
25 matrix is produced in a second step or, alternatively, multiple steps, by injection of the matrix material after removal of the iron core. This method is advantageous in that it is simple and well-suited for mass production.

A composition having the shape of a hollow cylinder may for example
30 be produced by extrusion, compression molding or injection molding. A composition having the shape of a hollow hemisphere may for example be produced by compression molding or by injection molding.

Production methods which involve co-extrusion (for the production of a composition having the shape of cylindrical rod) and extrusion (for

the production of a composition having the shape of a hollow cylinder) are especially advantageous, in that they are simple and inexpensive methods for the mass-production of the composition of the invention. The rod or tube which is produced by co-extrusion or
5 extrusion is then cut into smaller segments of an appropriate size. The composition may then be finished, for example by rounding the ends of the individual cylindrical rods or hollow cylinders.

The molten matrix material of compositions based on the use of a crystalline polymer will typically solidify considerably faster than
10 the matrix of a composition based on RTV rubber. Therefore, methods involving extrusion will often be more suitable for compositions comprising a crystalline polymer matrix, while compositions comprising a matrix of RTV rubber will typically more suitably be produced by e.g. injecting the material into pre-formed tubes.

15 The amount of active substance and the dimensions and specific form of the composition of the invention will of course vary according to the nature of the active substance in question as well as the intended use of the composition. The particular dose to be administered to a person or animal when the composition of the invention is a composition
20 for the delivery of a pharmaceutically active powder will thus depend on such factors as the condition and age of the patient and the particular condition to be treated.

The invention will be more fully described in the following, with reference to the accompanying drawings.

25 Fig. 1 shows a sectional side view of a coated cylindrical rod-shaped composition for the constant release of an active substance. The composition comprises an active substance which is substantially homogeneously distributed in a matrix 2, and is covered with a coating 1 which is open at one end. The coating 1 is substantially
30 insoluble in and impermeable to fluids such as body fluids during the intended release period. The matrix 2 is thus slowly eroded from the open end by the action of the aqueous medium in which the composition is employed, so that the surface area of the matrix 2 exposed to the

aqueous phase remains substantially constant with time, whereby the active substance is released at a constant and strictly controlled rate.

Fig. 2 shows the same composition as Fig. 1, with the exception that the composition is open at both ends, whereby the matrix 2 is eroded towards the center from each of the two open ends.

Fig. 3 shows a sectional side view of a coated cylindrical rod-shaped composition for pulsatile release of an active substance. The composition comprises alternating transverse layers of a matrix 2 and an active substance 3, and is covered with a coating 1 which is open at one end. The coating 1 is substantially insoluble in and impermeable to fluids such as body fluids during the intended release period. The matrix layers 2 are thus slowly eroded from the open end by the action of the aqueous medium in which the composition is employed, thereby releasing the active substance 3 in controlled bursts as each successive layer of the matrix 2 is eroded. Such a composition may also be prepared with an opening in both ends.

Fig. 4 shows a sectional side view of a composition for the release of two active substances. Several transverse layers containing a high concentration of an active substance 3 are arranged in a matrix 2 in which another active substance is uniformly distributed in a lower concentration, the composition being covered with a coating 1 which is substantially insoluble in and impermeable to fluids such as body fluids during the intended release period. The active substance contained in the matrix 2 is released at a substantially uniform rate, and the active substance contained in the layers 3 is released in bursts.

Fig. 5 shows a composition in the shape of a hollow cylinder. In this composition, the active substance is substantially homogeneously distributed in the matrix. The matrix will be eroded both from an interior surface 1 and an exterior surface 2 of the hollow cylinder, so that the surface area exposed to the fluid of the aqueous phase will remain substantially constant with time, whereby a

substantially zero order release of the active substance will be obtained.

Fig. 6 shows a composition in the shape of a hollow hemisphere, the active substance being substantially homogeneously distributed in the matrix. The matrix will be eroded both from an interior surface 1 and an exterior surface 2 of the hollow hemisphere, so that the surface area exposed to the fluid of the aqueous phase will remain substantially constant with time, whereby a substantially zero order release of the active substance will be obtained.

Fig. 7 shows a tablet-shaped composition, the active substance being substantially homogeneously distributed in the matrix. The matrix will mainly be eroded from the two relatively large flat surfaces, so that the surface area exposed to the fluid of the aqueous phase will remain substantially constant with time, whereby a substantially zero order release of the active substance will be obtained.

Fig. 8 shows a sectional side view of a cylindrical rod-shaped composition with a coating 2 which erodes at a substantially slower rate than the matrix 1 comprising the active substance. After a period of time in a fluid, the matrix 1 will have eroded from each end to 4, while the relatively slowly eroding coating 2 will have eroded to 3.

The invention is further disclosed in the following non-limiting examples.

EXAMPLE 1

Patent Blue was mixed thoroughly with a molten polyethylene glycol (PEG) 20,000 matrix material. The final matrix contained 25% Patent Blue and 75% PEG 20,000. While hot, the matrix was extruded into a pre-formed silicone tube with an internal diameter of 4 mm by means of a syringe and left to cool. The tube was then cut into segments with a length of about 2 cm to leave openings at either end of the dosage form through which release of the active substance may take place. The erosion rate in synthetic urine (1.94% urea, 0.8% MgSO_4 ,

0.11% CaCl_2 , 97.1% water) was measured over a period of 3 days to be 4 mm/24 h.

EXAMPLE 2

- By proceeding in a similar way as described in Example 1, but using a
- 5 matrix material composed of 90% PEG 20,000 and 10% PEG 400 monostearate with an HLB-value of 11.5, tube segments were prepared containing 75% of the matrix material and 25% Patent Blue. The erosion rate in synthetic urine was measured over a period of 8 days to be a constant 1.3 mm/24 h.
- 10 It could be seen in a microscope, using an enlargement of 50-125x, that there was a continuous crystalline phase comprising PEG 20,000, with the PEG 400 monostearate dispersed therein, the latter having been stained with the liposoluble blue colouring and therefore being
- 15 ly homogeneously distributed throughout the polymer crystals and at the same time to have filled in and "repaired" cracks and interfaces in and between the crystals.

EXAMPLE 3

- 10.8 g of PEG 35,000 and 3.6 g of PEG 400 monostearate were mixed
- 20 while heating at 60-80°C until molten. 9.6 g of microcrystalline theophylline were admixed with the molten matrix material until a uniform distribution thereof had been obtained. The molten matrix was extruded into a pre-formed teflon tube with an internal diameter of 6 mm and left to cool. The cooled matrix was then pushed from the
- 25 tube by means of a piston, and the resulting rod was coated with a 20% solution of polyurethane (Estane 5712 F 30) in acetone. The coated rod was subsequently cut into segments with a length of 20 mm.

- The release of theophylline from the resulting dosage forms was measured by immersing the dosage forms in 100 ml (34 g/l) of simulated intestinal juice (Revolyt; composition: 22 mmoles/l of hydrogen
- 30

carbonate, 15 mmoles/l of potassium, 60 mmoles/l of chloride, 3 mmoles/l of magnesium, 67 mmoles/l of sodium and 3 mmoles/l of sulphate) with constant shaking on an orbital shaker (64 rpm) at 37°C for 28 hours. Samples were taken every 2 hours and measured by high performance liquid chromatography (HPLC) in a Perkin Elmer HPLC apparatus.

Under these conditions, the release of theophylline was measured to be:

Release period (hours)		Amount released (μ moles/l)
10	0-2	1380
	2-4	1220
	4-6	940
	6-22	6520 ($\approx 815/2$ h)
	22-24	1055
15	24-26	850
	26-28	810

Under the same conditions, the rate of erosion of the matrix was 0.44 mm/h at either end of the dosage form.

EXAMPLE 4

25% of PEG 35,000, 12.5% of PEG 10,000 and 12.5% of PEG 400 mono-stearate were mixed while heating at 60-80°C. 49% of gentamycin sulphate (powder) and 1% of tartrazine were added to the molten matrix material until a uniform distribution thereof had been obtained. The molten matrix was extruded into a pre-formed teflon tube with an internal diameter of 5 mm and left to cool. The tube was then cut into segments of 20 mm in length.

The release of gentamycin sulphate from the resulting dosage forms was measured substantially as described in Example 3, except that release was measured spectrophotometrically using a Beckman DU-R spectrophotometer at 430 nm.

The release of gentamycin sulphate was measured over a period of 10 hours to be 10-15 mg/h, and the rate of erosion of the matrix was 1 mm/h.

EXAMPLE 5

5 36% of PEG 35,000 and 24% of PEG 400 monostearate were mixed while heating at 60-80°C. 39% of gentamycin sulphate (powder) and 1% of Patent Blue V were added to the molten matrix material until a uniform distribution thereof had been obtained. The molten matrix was extruded into a pre-formed teflon tube with an internal diameter of
10 5 mm and left to cool. The tube was then cut into segments of 20 mm in length.

The release of gentamycin sulphate from the resulting dosage forms was measured substantially as described in Example 4, except that the release was measured at 638 nm, to be 10-14 mg/h over a period of 8
15 hours.

EXAMPLE 6

By proceeding in a similar way as described in Example 5, but using PEG 35,000 and PEG 400 monostearate as the matrix material and neomycin sulphate as the active substance, tube segments were prepared
20 containing 33.3% PEG 35,000, 33.3% PEG 400 monostearate, 32.3% neomycin sulphate and 1% tartrazine.

The release of neomycin sulphate from the resulting dosage forms was measured as described in Example 4 to be 8-10 mg/h, and the erosion rate of the matrix was 2 mm/6 h at either end.

25 EXAMPLE 7

8 g of a block copolymer of ethylene oxide and propylene oxide (Synperonic F-88 from ICI) and 2 g of polyethylene glycol 400 monostearate

te were mixed while heating at 60-80°C until molten. 2 g of Patent Blue V were admixed with the molten matrix material, and the mixture was extruded into a pre-formed teflon tube (diameter 4 mm) and left to cool. The tube was then cut into 20 mm long segments, which were left open at both ends. The erosion rate in synthetic urine was measured to be a constant 1.2 mm/24 h over a period of 8 days.

EXAMPLE 8

- 0.38 g of D6210 (1,3-divinyldimethyltetramethylsiloxane, obtained from Petrarch) was mixed with 4 g of methylhydro-dimethylsiloxane copolymer (PS 123, obtained from Petrarch) at room temperature. To the mixture was added 3 g of Salsorb 84 (a modified polyacrylic acid, particle size 90-850 μ m, capacity (in 0.9% NaCl): 45 g/g; obtained from Allied Colloids Ltd.) followed by addition of 4.72 g of erythromycin estolate, 0.4 g of a catalyst solution (0.03% platinum in 10% cyclic vinylmethylsiloxanes and 90% vinyltrimethylterminated polydimethylsiloxane) and 1% Patent Blue and thorough mixing. The matrix mixture was extruded into a pre-formed teflon tube with an internal diameter of 6 mm and left to harden for up to 4 hours at room temperature. The tubes were then cut into segments of 20 mm in length.
- 20 The release of erythromycin estolate from the resulting dosage forms was measured essentially as described in Example 3 with the exception that the dosage forms were immersed in 100 ml of simulated gastric juice (pepsin-HCl, pH 3) (to which simulated intestinal juice as described above had been added as a buffer).
- 25 Using Patent Blue as an indicator, the release was measured to be 9-10 mg/h of erythromycin estolate decreasing to about 7 mg/h over 24 hours. Under the same conditions, the rate of erosion of the matrix was 16.5 mm/24 hours.

EXAMPLE 9

0.19 g of 1,3-divinyldimethyltetramethylsiloxane (D6210 from Petrarch) was mixed with 2 g of methylhydro-dimethylsiloxane copolymer (PS123 from Petrarch) at room temperature. To the mixture was added 5 g of carboxy-methyl-cellulose (A250 from Aqualon), followed by addition of 5 g of gentamycin sulphate and 0.4 g of a catalyst solution (0.03% platinum in 10% cyclic vinylmethylsiloxanes and 90% vinyltrimethyl-terminated polydimethylsiloxane). The matrix was extruded into a pre-formed teflon tube with an internal diameter of 4 mm and left to harden for up to 2 hours at room temperature. The tubes were then cut into segments of 20 mm in length.

The release of gentamycin sulphate in simulated gastric juice was measured as in Example 8 to be 1.3 mg/h. The rate of erosion of the matrix was 6 mm/24 h.

15 EXAMPLE 10

Comparative examples with various compositions

a) A composition containing pure PEG was prepared by extruding molten PEG 10,000 into a pre-formed teflon tube (diameter 4 mm). After cooling, the matrix was pushed from the tube by means of a piston, and the resulting rod was coated with a 20% solution of polyurethane (Estane 5712 F 30) in acetone. The coated rod was subsequently cut into segments having a length of 10 mm. The erosion rate of the PEG in simulated intestinal juice (Example 3) was 4 mm/h.

b) A composition was prepared and the erosion rate measured as in a) above, with the exception that the PEG was PEG 35,000. The erosion rate was 1.8 mm/h.

c) A mixture of 95% PEG 35,000 and 5% PEG 400 monostearate was melted and a coated rod was prepared as in a) above, using pre-formed teflon tubes with a diameter of 6 mm. The erosion rate in simulated intestinal juice was measured to be 1.45 mm/h.

d) A mixture of 75% PEG 35,000 and 25% PEG 400 monostearate was melted. Dextrin was added as a filler in an amount of 40% of the total weight of the composition. The resulting mixture was extruded into pre-formed teflon tubes (diameter 10 mm) and coated rods were prepared as in a) above. The erosion rate in simulated intestinal juice was measured to be 0.34 mm/h.

e) A mixture of 75% PEG 35,000 and 25% PEG 400 monostearate was melted. To the molten mixture was added a mixture of dextrin as a filler and morphine hydrochloride as an active substance, the amount of dextrin and morphine hydrochloride being 40% of the total weight of the composition. The composition, which contained 3.55% morphine hydrochloride, was extruded into pre-formed teflon tubes (diameter 6 mm). The rods were coated as in a) and cut into 10 mm segments. The release of morphine hydrochloride in simulated intestinal juice was measured by HPLC to be 1 mg/h over a period of 10 hours, and the erosion rate was measured to be 0.43 mm/h.

f) A composition was prepared as in e) above, with the exception that the content of morphine hydrochloride was 9.54%. Release of morphine hydrochloride in simulated intestinal juice was measured by HPLC to be 3 mg/h over a period of 10 hours, and the erosion rate was measured to be 0.48 mm/h.

g) A mixture of 75% PEG 35,000 and 25% PEG 400 monostearate was melted and mixed with tartrazine in an amount of 3.55%. The mixture was extruded into pre-formed teflon tubes (diameter 6 mm), coated as in a) and cut into 12 mm segments. The erosion rate in simulated intestinal juice was measured to be a constant 1.5 mm/h from each end over a period of 4 hours.

h) 10.5 g of PEG 35,000 and 3.5 g PEG 400 monostearate were melted and mixed together. 6.0 g of methotrexate was added, resulting in a mixture comprising 52.2% PEG 35,000, 17.5% PEG 400 monostearate and 30% methotrexate (MTX). The molten mixture was extruded into pre-formed teflon tubes (diameter 4 mm), and coated rods were prepared as in a). Release of MTX in synthetic urine (Example 1) was measured by

HPLC to be a constant 1.5 mg/h over a period of 10 hours, and the erosion rate was 0.5 mm/h.

- 5 i) 5.4 g of PEG 35,000 and 1.8 g PEG 400 monostearate were melted and mixed with 4.8 g of dextrin/tartrazin (99:1). The mixture was extruded into pre-formed teflon tubes (diameter 6 mm) and coated as in a). Erosion in simulated intestinal juice was measured with a spectrophotometer at a wavelength of 430 nm to be 0.34 mm/h over a period of 12 hours.
- 10 j) 1 g of PEG 35,000, 0.5 g of PEG 400 monostearate and 1 g of a diacetylated tartaric acid ester of mono- and diglycerides (Dat-S from Grindsted Products, Denmark) were melted together. 2.5 g of sucralfate was then added and the mixture was extruded into pre-formed teflon tubes (diameter 6 mm). Erosion in simulated intestinal juice was measured to be 1 mm in 8 hours.
- 15 k) A composition similar to that of j) was prepared, but without the diacetylated tartaric acid ester. 4 g of PEG 35,000 and 2 g of PEG 400 monostearate were melted, and 4 g of sucralfate was added to the molten mixture. The mixture was extruded into pre-formed teflon tubes (diameter 6 mm) and coated as in a). Erosion in simulated intestinal
- 20 juice was greater than 2 mm in 8 hours.
- 25 l) 5 g of PEG 35,000 were melted and extruded into a pre-formed teflon tube (diameter 6 mm). One end of the tube was dipped in molten PEG 1500 containing 10% tartrazine. The composition was removed from the tube and coated with Estane F30, the end which had been dipped in the mixture of PEG 1500 and tartrazine also being coated. The composition was then cut to a length of 7.5 mm. Erosion in simulated intestinal juice resulted in a yellow colouration of the liquid after 4 hours, which showed that the erosion rate was about 1.9 mm/h.
- 30 m) 2.25 g of PEG 35,000 and 0.75 g of PEG 400 monostearate were melted, 2 g of dextrin was added (40% dextrin), and the mixture was extruded into a pre-formed teflon tube (diameter 6 mm). Following the procedure of l) above, 3.5 mm long coated rods with PEG 1500 + tartrazine at the coated end were prepared and subsequently eroded in

simulated intestinal juice. Yellow colouration was seen after 8 hours, which showed that the erosion rate was about 0.23 mm/h.

EXAMPLE 11

An composition was prepared as described in Example 3, with the exception that the rods were cut into segments having a length of 12 mm. The resulting rods contained 195 mg PEG 35,000, 65 mg PEG 400 monostearate and 170 mg microcrystalline theophyllin. The *in vitro* erosion rate, measured as described in Example 3, was determined to be 1 mm/h, corresponding to approximately 15 mg theophyllin released per hour. The exact amount of theophyllin released, as determined by HPLC, was as follows:

	Release period (hours)	Amount released (μ moles/l)
	0-2	2575
	2-4	1740
15	4-6	1645
	6-8	1740

The *in vivo* release of theophyllin from this composition was tested in six patients, 3 males and 3 females, aged 18-42 years (mean age 30 years), weighing from 63 to 85 kg (mean weight 66 kg), all of whom were diagnosed as having bronchial asthma.

The first dose was given to the patients before breakfast (i.e. in the fasting state) as two units of the composition (340 mg theophyllin) together with 100 ml of liquid. The second dose was given at least three days later in the morning as an i.v. injection of theophyllin (Theo-Dur 20 mg/ml) over a period of 10 minutes, in a dose of 5 mg/kg ideal body weight, in order to determine the serum half-life of theophyllin in the individual patients. Following the oral dose, venous blood samples were drawn at 0, 1, 2, 3, 4, 6, 8, 10, 12, 14, 16 and 24 hours. Serum samples were drawn at 0, 15 min., 30 min., 60 min., 90 min., and 2, 3, 5, 7, 9 and 11 hours after the i.v. dose. The serum portion of the blood specimen was immediately frozen at

-20°C and kept frozen until analyzed 2 weeks later. The amount of theophyllin in the serum was assayed by HPLC with an accuracy of $\pm 5\%$. The measured serum levels together with the calculated serum half-life of theophyllin in the individual patients are shown in the following table:

Patient No.	Serum half-life (hours)	Theophyllin in serum ($\mu\text{moles/l}$)											
		Hours											
		1	2	3	4	6	8	10	12	14	16	24	
10		<hr/>											
	1	6	21	21	-	22	21	20	17	16	14	11	9
	2	9	7	16	24	30	36	32	30	32	30	25	19
	3	8	25	38	39	39	39	44	51	50	45	41	30
	4	9	11	19	22	26	39	33	29	26	21	19	15
15	5	7	9	14	19	20	25	21	19	22	16	14	8
	6	8	9	21	19	18	20	21	21	22	26	25	18
		<hr/>											

EXAMPLE 12

The *in vivo* release of morphine hydrochloride from the composition of Example 10 e) was tested in two individuals, both healthy males aged 40 years, weighing 85 kg (patient 1) and 65 kg (patient 2). The composition, which contained 10 mg of morphine hydrochloride, was taken together with 100 ml of liquid two hours after breakfast. Concentrations of morphine hydrochloride in serum were determined every second hour by drawing venous blood samples, which were then kept cold until the next day, when the serum portion was separated and frozen at -20°C. The concentration of morphine hydrochloride in the serum was analyzed three weeks later by using a RIAS method, which determines both free and conjugated morphine hydrochloride with an accuracy of $\pm 5\%$ and with a sensitivity of 2 ng total morphine hydrochloride/ml serum. The following concentrations of morphine hydrochloride in serum were found:

Morphine hydrochloride in serum (ng/ml)

Hours:		1	2	4	6	8	10	12	14	21
Patient 1		18	32	44	46	42	51	76	60	34
5	Patient 2	35	76	64	44	31	21	27	-	-

EXAMPLE 13

- 18% of PEG 20,000, 27% of PEG 35,000 and 15% of PEG 400 monostearate were mixed while heating at 65-75°C, and 40% of gentamycin sulphate was added to the molten matrix material and mixed until uniformly distributed. The molten mixture was extruded into a pre-formed teflon tube (diameter 4 mm) and left to cool. The resulting rod was then pushed from the tube by means of a piston and the rod was cut into pieces with a length of 15 or 30 mm and dip-coated with a 20% solution of Estane 30, leaving one end uncoated. The release of gentamycin sulphate from the resulting composition was measured *in vitro* substantially as described in Example 3, and by using a biological agar hole diffusion method for the assaying of gentamycin sulphate. A release of gentamycin sulphate of 14 mg/72 hours was found.
- 20 The erosion rate from the open end of the composition was measured to be 1 mm/24 hours, corresponding to a release of 5 mg of gentamycin sulphate/24 hours.

The composition as described above was glued on the tip of a urinary balloon catheter (Ruch, ZF, 5 ml; size 12). The diameter of the tip was similar to that of the catheter, and the length of the composition was 30 mm.

The *in vivo* release was examined in an animal model. A female pig, SPR Danish landrace x Yorkshire LYY, weighing 22 kg, was used. The pig was housed in a wire mesh cage with a stainless steel tray for collection of urine. The catheter was introduced into the urine

bladder while the pig was anesthetized with Sedaperone (i.m.) and Hypnodil (i.p.). Atropin (i.m.) was given at the time to prevent salivation. 20 ml aliquots of urine were collected from the tray every 24 hours and the concentration of gentamycin sulphate in the urine was determined by using a biological agar hole diffusion method with a sensitivity of 0.2 μ g gentamycin sulphate/mg urine. The following concentrations of gentamycin sulphate were found:

μ g gentamycin sulphate/ml urine		
	0-24 hours:	1.75
10	24-48 hours:	1.40
	48-72 hours:	1.55

At autopsy on day 4 there was a slight haemorrhage on the outside of the bladder. The mucosa of the bladder and urethra were found to be normal.

15 EXAMPLE 14

An animal study using a pig as described above (Example 13) was repeated using the same composition. In this study, an Argyle silicone balloon catheter (12 ch, 5 ml, lot No. 027603) was used. Each catheter was equipped with a cylindrical 15 mm long composition, and the diameter of the tip was similar to that of the catheter. The study lasted for a period of 7 days. Two pigs (weighing 20 and 21 kg) were used. The following concentrations of gentamycin sulphate were found:

		μg gentamycin sulphate/ml urine	
Day after catheter insertion		Pig 1	Pig 2
5	1	2.9	1.25
	2	4.7	0.25
	3	4.6	0.95
	4	3.4	0.27
	5	5.3	0.59
	6	-	1.25
10	7	-	3.40

The release of gentamycin sulphate from the device was probably blocked in pig 1 from day 5, since the composition was only half-emptied when the catheter was removed on day 7.

At autopsy on day 8 there were signs of mucosal tissue irritation in the trigonum area of pig 1, which was probably caused by the presence of the tip of the catheter in the bladder. The bladder mucosa and urethral mucosa were found to be normal in pig 2.

CLAIMS

1. A composition for controlled delivery of an active substance into an aqueous phase by erosion at a substantially constant rate of a surface or surfaces of the composition, the composition comprising
- 5 a matrix of a substantially water soluble crystalline polymer or a mixture of substantially water soluble crystalline polymers,
- a surface active agent or a mixture of surface active agents dispersed in the crystalline polymer phase in an amount of 0-50% by weight of the crystalline polymer and surface active agent,
- 10 the surface active agent comprising a compound or compounds having at least one domain which is compatible with the crystalline polymer phase and at least one other domain which is substantially lipophilic, and having a melting point which is lower than that of the crystalline polymer,
- 15 at least one active substance substantially homogeneously dispersed in the crystalline polymer phase and/or dispersed in the surface active agent and/or located in geometrically well-defined zones within the composition, and
- optionally, a filler,
- 20 the surface active agent and/or the active substance reducing the water affinity of domains between grains and in cracks in the crystalline polymer matrix and in the crystalline polymer matrix itself, thereby substantially eliminating water diffusion in the interface between the polymer crystals, so that the erosion is pre-
- 25 dominantly effected by the dissolving action of an aqueous medium on a surface or surfaces of the composition exposed to the medium.
2. A composition according to claim 1, wherein the crystalline polymer matrix comprises a polyglycol.

3. A composition according to claim 1 or 2, wherein the matrix comprises a homopolymer and/or a copolymer.
4. A composition according to any of the preceding claims, wherein the matrix comprises a polyethylene glycol and/or a block copolymer
5 of ethylen oxide and propylene oxide.
5. A composition according to claim 4, wherein the block copolymer comprises up to about 30% by weight of the propylene oxide based block, and has a molecular weight of above about 5000 daltons, typically about 5000 to about 30,000 daltons, more typically about 8000
10 to about 15,000 daltons.
6. A composition according to any of the preceding claims, wherein the crystalline polymer matrix comprises polyethylene glycol with a molecular weight of from about 2000 to about 500,000 daltons, typically from about 5000 to about 100,000 daltons, more typically from
15 about 10,000 to about 50,000 daltons, and especially from about 20,000 to about 35,000 daltons.
7. A composition according to any of the preceding claims, wherein the crystalline polymer matrix has a melting point of about 20-120°C, typically about 30-100°C, more typically about 40-80°C.
- 20 8. A composition according to any of the preceding claims, wherein the active substance is present in an amount of up to about 60%, typically up to about 50%, by weight of the composition.
9. A composition according to any of the preceding claims, which comprises as a filler dextrin, sucralfate, calcium hydroxyl-apatite,
25 calcium phosphate or a fatty acid salt such as magnesium stearate.
10. A composition according to any of the preceding claims, wherein the combination of the filler and the active substance comprises up to about 60%, typically up to about 50%, by weight of the composition.

11. A composition according to any of the preceding claims, wherein the active substance is a drug for human or veterinary use, a vitamin or other nutritional supplement, a disinfectant, a deodorant or another substance to be administered continuously in an aqueous environment.
12. A composition according to any of the preceding claims, wherein the active substance is a pharmaceutically active powder.
13. A composition according to claim 12, wherein the powder has a particle size of from about 0.1 μm to about 500 μm , typically from about 0.5 μm to about 300 μm , more typically from about 1 μm to about 200 μm , especially from about 5 μm to about 100 μm .
14. A composition according to any of the preceding claims, wherein the surface active agent is a non-ionic emulsifier comprising one or more fatty acid esters and/or fatty acid ethers.
15. A composition according to any of the preceding claims, wherein the surface active agent comprises a fatty acid ester and/or fatty acid ether having carbon chains of from 12 to 24 carbon atoms, typically from 12 to 20 carbon atoms.
16. A composition according to any of the preceding claims, wherein the surface active agent comprises an ester and/or ether of palmitic acid or stearic acid.
17. A composition according to any of the preceding claims, wherein the surface active agent comprises a polyglycol ester or ether, a polyethylene glycol ester or ether, a polyhydroxy ester or ether and/or a sugar ester or ether such as a sorbitan ester or ether.
18. A composition according to any of the preceding claims, wherein the surface active agent comprises a polyethylene glycol monostearate, in particular polyethylene glycol 400 monostearate.
19. A composition according to any of the preceding claims, wherein the surface active agent is present in an amount of about 2-50%, e.g.

about 5-50%, typically about 10-40%, more typically about 15-35%, such as about 20-30%, by weight of the crystalline polymer and surface active agent.

20. A composition according to any of the preceding claims which has
5 a geometric shape enabling a substantially constant surface area to become exposed during erosion of the matrix.

21. A composition according to claim 20 which has the shape of a
cylindrical rod, and which is provided with a coating which is sub-
stantially insoluble in and impermeable to fluids such as body fluids
10 during the intended release period, the coating having an opening at one or both ends.

22. A composition according to claim 21, wherein the coating compri-
ses a matrix of one or more substantially water soluble crystalline
polymers and a surface active agent, the coating being one which is
15 eroded in the aqueous phase at a substantially slower rate than the matrix material comprising the active substance, whereby a sub-
stantially constant area of the matrix comprising the active sub-
stance is exposed during erosion of the composition, and whereby the
coating is substantially eroded upon erosion of the matrix comprising
20 the active substance.

23. A composition according to claim 21, wherein the coating is one
which disintegrates or crumbles after erosion of the matrix.

24. A composition according to claim 20 which has the shape of a
hollow cylinder.

25 25. A composition according to claim 20 which has the shape of a
hollow hemisphere.

26. A composition according to claim 20 which has the shape of a
tablet or slab.

27. A composition according to any of the preceding claims, wherein

the active substance is substantially homogeneously dispersed in the crystalline polymer matrix.

28. A composition according to any of the preceding claims, wherein the active substance has at least one domain which is compatible with
5 the crystalline polymer phase and at least one other domain which is substantially lipophilic, the active substance being substantially homogeneously dispersed in the crystalline polymer phase.

29. A composition according to claim 28, wherein the surface active agent is present in the matrix in an amount of about 0-2% by weight
10 of the matrix.

30. A composition according to claim 21, comprising alternating substantially transverse layers of

a layer comprising the crystalline polymer matrix and the surface active agent, and optionally comprising the active ingredient
15 substantially homogeneously dispersed in the matrix, and

a layer comprising the active ingredient, the active ingredient optionally being substantially homogeneously dispersed in the crystalline polymer and the surface active agent.

31. A composition according to claim 30, wherein the alternating
20 layers comprise, respectively, two or more different active substances.

32. Use of a composition according to any of the preceding claims in the preparation of a multiple units pharmaceutical formulation, e.g. in the form of a capsule or tablet.

25 33. A composition for controlled delivery of an active substance into an aqueous phase, the composition comprising

a matrix of room-temperature vulcanizing rubber (RTV rubber) in which particles of a superabsorbent polymer are substantially homogeneously distributed, the superabsorbent polymer particles

also being present substantially near the surface of the composition, and

at least one active substance substantially homogeneously dispersed in the matrix and/or located in geometrically well-defined zones within the matrix,

in which the liquid of the aqueous phase is able to diffuse into the matrix at a limited rate, resulting in swelling of the superabsorbent polymer particles and the localized disruption of the matrix in the vicinity of the swollen particles, whereby the active substance is released in a specifically controlled manner according to its distribution in the matrix.

34. A composition according to claim 33, wherein the RTV rubber comprises one or two component RTV silicon elastomers based on polydimethylsiloxane.

35. A composition according to claim 33 or 34, which comprises a catalyst and, optionally, a cross-linking agent.

36. A composition according to any of claims 33 to 35, wherein the superabsorbent polymer particles are able to remain in a semi-solid state upon absorption of water or other liquids, and are able to absorb at least about 10 times their own weight in water, typically at least about 100 times their own weight in water, especially at least about 200 times their own weight in water.

37. A composition according to any of claims 33 to 36, wherein the superabsorbent polymer particles are able to remain in a semi-solid state upon absorption of bodily fluids, and are able to absorb at least about 5 times their own weight in bodily fluids, typically at least about 20 times their own weight in bodily fluids, especially at least about 40 times their own weight in bodily fluids.

38. A composition according to any of claims 33 to 37 wherein the superabsorbent polymer comprises polyacrylic acid, modified poly-

acrylic acid, carboxymethyl cellulose, modified carboxymethyl cellulose and/or cross-linked polyvinyl pyrrolidone.

39. A composition according to any of claims 33 to 38 wherein the superabsorbent polymer is present in an amount of about 5-75%, typically about 10-50%, more typically about 20-25% by weight of the matrix.

40. A composition according to any of claims 33 to 39 wherein the active substance is present in an amount of up to about 60%, typically up to about 50%, by weight of the composition.

41. A composition according to any of claims 33 to 40 wherein the active substance is a drug for human or veterinary use, a vitamin or other nutritional supplement, a disinfectant, a deodorant or another substance to be administered continuously in an aqueous environment.

42. A composition according to any of claims 33 to 41 wherein the active substance is a pharmaceutically active powder.

43. A composition according to claim 42, wherein the powder has a particle size of from about 0.1 μm to about 500 μm , typically from about 0.5 μm to about 300 μm , more typically from about 1 μm to about 200 μm , especially from about 5 μm to about 100 μm .

44. A composition according to any of claims 33 to 43 which has a geometric shape enabling a substantially constant surface area to become exposed during erosion of the matrix.

45. A composition according to claim 44 which has the shape of a cylindrical rod, and which is provided with a coating which is substantially insoluble in and impermeable to fluids such as body fluids during the intended release period, the coating having an opening at one or both ends.

46. A composition according to claim 44 which has the shape of a hollow cylinder.

47. A composition according to claim 44 which has the shape of a hollow hemisphere.
48. A composition according to claim 44 which has the shape of a tablet or slab.
- 5 49. A composition according to any of claims 33 to 48, wherein the active substance is substantially homogeneously dispersed in the matrix.
50. A composition according to claim 45, comprising alternating substantially transverse layers of
- 10 a layer comprising the matrix, and optionally comprising the active ingredient substantially homogeneously dispersed in the matrix, and
- a layer comprising the active ingredient, the active ingredient optionally being substantially homogeneously distributed in
- 15 matrix material.
51. A composition according to claim 50, wherein the alternating layers comprise, respectively, two or more different active substances.
52. Use of a composition according to any of claims 33 to 51 in the
- 20 preparation of a multiple units pharmaceutical formulation, e.g. in the form of a capsule or tablet.
53. A method for preparing a composition for controlled delivery of an active substance into an aqueous phase by erosion at a substantially constant rate of a surface or surfaces of the
- 25 composition, the method comprising
- combining a substantially water soluble crystalline polymer or a mixture of substantially water soluble crystalline polymers,

a surface active agent or a mixture of surface active agents in an amount of 0-50% by weight of the crystalline polymer and surface active agent, the surface active agent comprising a compound or compounds having at least one domain which is compatible with the crystalline polymer phase and at least one other domain which is substantially lipophilic, and having a melting point which is lower than that of the crystalline polymer,

at least one active substance, and

optionally, a filler,

to form a matrix comprising the surface active agent or the mixture of surface active agents dispersed in the crystalline polymer phase and the active substance substantially homogeneously dispersed in the crystalline polymer phase and/or dispersed in the surface active agent and/or located in geometrically well-defined zones within the composition, whereby the surface active agent and/or the active substance reduces the water affinity of domains between grains and in cracks in the crystalline polymer matrix and in the crystalline polymer matrix itself, thereby substantially eliminating water diffusion in the interface between the polymer crystals, so that erosion in an aqueous phase is predominantly effected by the dissolving action of an aqueous medium on a surface or surfaces of the composition exposed to the medium.

54. A method according to claim 53, wherein the crystalline polymer and the surface active agent are mixed while heating at a temperature sufficient to melt the polymer, and while stirring, so as to obtain a substantially homogeneous mixture, the active substance being added to the molten mixture of the polymer and the surface active agent or added to the mixture prior to heating, whereupon the resulting mixture is shaped and allowed to cool.

55. A method according to claim 53 or 54, wherein the composition is shaped by extrusion, co-extrusion, injection molding or compression molding.

56. A method according to any of claims 53 to 55, wherein the crystalline polymer comprises a polyglycol.
57. A method according to any of claims 53 to 56, wherein the crystalline polymer is a homopolymer and/or a copolymer.
- 5 58. A method according to any of claims 53 to 57, wherein the crystalline polymer comprises a polyethylene glycol and/or a block copolymer of ethylene oxide and propylene oxide.
59. A method according to claim 58, wherein the block copolymer comprises up to about 30% by weight of the propylene oxide based
10 block, and has a molecular weight of above about 5000 daltons, typically about 5000 to about 30,000 daltons, more typically about 8000 to about 15,000 daltons.
60. A method according to any of claims 53 to 59, wherein the crystalline polymer matrix comprises polyethylene glycol with a
15 molecular weight of from about 2000 to about 500,000 daltons, typically from about 5000 to about 100,000 daltons, more typically from about 10,000 to about 50,000 daltons, and especially from about 20,000 to about 35,000 daltons.
61. A method according to any of claims 53 to 60, wherein the
20 crystalline polymer matrix has a melting point of about 20-120°C, typically about 30-100°C, more typically about 40-80°C.
62. A method according to any of claims 53 to 61, wherein the active substance is added in an amount of up to about 60%, typically up to about 50%, by weight of the composition.
- 25 63. A method according to any of claims 53 to 62, wherein a filler such as dextrin, sucralfate, calcium hydroxyl-apatite, calcium phosphate or a fatty acid salt such as magnesium stearate is added to the mixture of the crystalline polymer and the surface active agent either before or after heating.

64. A method according to any of claims 53 to 63, wherein the the filler and the active substance are added in a combined amount of up to about 60%, typically up to about 50%, by weight of the composition.
- 5 65. A method according to any of claims 53 to 64, wherein the active substance is a drug for human or veterinary use, a vitamin or other nutritional supplement, a disinfectant, a deodorant or another substance to be administered continuously in an aqueous environment.
- 10 66. A method according to any of claims 53 to 65, wherein the active substance is a pharmaceutically active powder.
67. A method according to claim 66, wherein the powder has a particle size of from about 0.1 μm to about 500 μm , typically from about 0.5 μm to about 300 μm , more typically from about 1 μm to about 200 μm , especially from about 5 μm to about 100 μm .
- 15 68. A method according to any of claims 53 to 67, wherein the surface active agent is a non-ionic emulsifier comprising one or more fatty acid esters and/or fatty acid ethers.
- 20 69. A method according to any of claims 53 to 68, wherein the surface active agent comprises a fatty acid ester and/or fatty acid ether having carbon chains of from 12 to 24 carbon atoms, typically from 12 to 20 carbon atoms.
70. A method according to any of claims 53 to 69, wherein the surface active agent comprises an ester and/or ether of palmitic acid or stearic acid.
- 25 71. A method according to any of claims 53 to 70, wherein the surface active agent comprises a polyglycol ester or ether, a polyethylene glycol ester or ether, a polyhydroxy ester or ether and/or a sugar ester or ether such as a sorbitan ester or ether.
72. A method according to any of claims 53 to 71, wherein the surface

active agent comprises a polyethylene glycol monostearate, in particular polyethylene glycol 400 monostearate.

73. A method according to any of claims 53 to 72, wherein the surface active agent is added in an amount of about 2-50%, e.g. about 5-50%, typically about 10-40%, more typically about 15-35%, such as about 20-30%, by weight of the crystalline polymer and surface active agent.

74. A method according to any of claims 53 to 73, wherein the composition is formed into a geometric shape enabling a substantially constant surface area to become exposed when the matrix is eroded in an aqueous phase.

75. A method according to claim 74, wherein the composition is formed into the shape of a cylindrical rod and provided with a coating which is substantially insoluble in and impermeable to fluids such as body fluids during the intended release period, the coating having an opening at one or both ends.

76. A method according to claim 75, wherein the composition is formed by co-extrusion of the coating with the matrix and the active substance, or by injection molding, compression molding or extrusion of the matrix and the active substance followed by dip coating or solvent coating by spraying or dipping.

77. A method according to claim 75 or 76, wherein the coating comprises a matrix of one or more substantially water soluble crystalline polymers and a surface active agent, the coating being one which is eroded in the aqueous phase at a substantially slower rate than the matrix material comprising the active substance, whereby a substantially constant area of the matrix comprising the active substance is exposed during erosion of the composition, and whereby the coating is substantially eroded upon erosion of the matrix comprising the active substance.

78. A method according to claim 75 or 76, wherein the coating is one which disintegrates or crumbles after erosion of the matrix.

79. A method according to claim 74, wherein the composition is formed into the shape of a hollow cylinder.
80. A method according to claim 74, wherein the composition is formed into the shape of a hollow hemisphere.
- 5 81. A method according to claim 74, wherein the composition is formed into the shape of a tablet or slab.
82. A method according to any of claims 53 to 81, wherein the active substance becomes substantially homogeneously dispersed in the crystalline polymer matrix.
- 10 83. A method according to any of claims 53 to 82, wherein the active substance has at least one domain which is compatible with the crystalline polymer phase and at least one other domain which is substantially lipophilic, the active substance becoming substantially homogeneously dispersed in the crystalline polymer phase.
- 15 84. A method according to claim 83, wherein the surface active agent is added to the matrix material in an amount of about 0-2% by weight of the matrix.
85. A method according to claim 75, wherein the composition is formed by injecting or extruding alternating substantially transverse
- 20 layers of
- a layer comprising the crystalline polymer matrix and the surface active agent, the active ingredient optionally being substantially homogeneously dispersed in the matrix, and
- a layer comprising the active ingredient, the active ingredient
- 25 optionally being substantially homogeneously dispersed in the crystalline polymer and the surface active agent.
86. A method according to claim 85, wherein the alternating layers comprise, respectively, two or more different active substances.

87. A method for preparing a multiple units pharmaceutical formulation for controlled delivery of an active substance, the method comprising combining in the form of a capsule or tablet a multiplicity of individual units of a composition prepared according to any of claims 53 to 86.

88. A method for preparing a composition for controlled delivery of an active substance into an aqueous phase, the method comprising combining a room-temperature vulcanizing rubber (RTV rubber) with particles of a superabsorbent polymer and at least one active substance to form a matrix in which the superabsorbent polymer particles are substantially homogeneously distributed and also present substantially near the surface of the composition, and in which the active substance is substantially homogeneously dispersed and/or located in geometrically well-defined zones within the matrix, so that a liquid of an aqueous phase is able to diffuse into the matrix at a limited rate, resulting in swelling of the superabsorbent polymer particles and the localized disruption of the matrix in the vicinity of the swollen particles, whereby the active substance is released in a specifically controlled manner according to its distribution in the matrix.

89. A method according to claim 88, wherein a catalyst and, optionally, a cross-linking agent is added to the matrix material.

90. A method according to claim 88 or 89, wherein the RTV rubber material, the superabsorbent polymer, and the catalytic accelerator and/or cross-linking agent are mixed together at room temperature while stirring, the active substance being added to the mixture before or while stirring, whereupon the mixture is shaped.

91. A method according to any of claims 88 to 90, wherein the composition is shaped by extrusion, co-extrusion, injection molding or compression molding.

92. A method according to any of claims 88 to 91, wherein the RTV

rubber comprises one or two component RTV silicon elastomers based on polydimethylsiloxane.

93. A method according to any of claims 88 to 92, wherein the superabsorbent polymer particles are able to remain in a semi-solid state upon absorption of water or other liquids, and are able to absorb at least about 10 times their own weight in water, typically at least about 100 times their own weight in water, especially at least about 200 times their own weight in water.

94. A method according to any of claims 88 to 93, wherein the superabsorbent polymer particles are able to remain in a semi-solid state upon absorption of bodily fluids, and are able to absorb at least about 5 times their own weight in bodily fluids, typically at least about 20 times their own weight in bodily fluids, especially at least about 40 times their own weight in bodily fluids.

95. A method according to any of claims 88 to 94, wherein the superabsorbent polymer comprises polyacrylic acid, modified polyacrylic acid, carboxymethyl cellulose, modified carboxymethyl cellulose and/or cross-linked polyvinyl pyrrolidone.

96. A method according to any of claims 88 to 95, wherein the superabsorbent polymer is added in an amount of about 5-75%, typically about 10-50%, more typically about 20-25% by weight of the matrix.

97. A method according to any of claims 88 to 96, wherein the active substance is added in an amount of up to about 60%, typically up to about 50%, by weight of the composition.

98. A method according to any of claims 88 to 97, wherein the active substance is a drug for human or veterinary use, a vitamin or other nutritional supplement, a disinfectant, a deodorant or another substance to be administered continuously in an aqueous environment.

99. A method according to any of claims 88 to 98, wherein the active substance is a pharmaceutically active powder.

100. A method according to claim 99, wherein the powder has a particle size of from about 0.1 μm to about 500 μm , typically from about 0.5 μm to about 300 μm , more typically from about 1 μm to about 200 μm , especially from about 5 μm to about 100 μm .
- 5 101. A method according to any of claims 88 to 100, wherein the composition is formed into a geometric shape enabling a substantially constant surface area to become exposed when the matrix is eroded in an aqueous phase.
- 10 102. A method according to claim 101, wherein the composition is formed into the shape of a cylindrical rod and provided with a coating which is substantially insoluble in and impermeable to fluids such as body fluids during the intended release period, the coating having an opening at one or both ends.
- 15 103. A method according to claim 102, wherein the composition is formed by co-extrusion of the coating with the matrix and the active substance, or by injection molding, compression molding or extrusion of the matrix and the active substance followed by either dip coating or solvent coating by spraying or dipping.
- 20 104. A method according to claim 101, wherein the composition is formed into the shape of a hollow cylinder.
105. A method according to claim 101, wherein the composition is formed into the shape of a hollow hemisphere.
106. A method according to claim 101, wherein the composition is formed into the shape of a tablet or slab.
- 25 107. A method according to any of claims 88 to 106, wherein the active substance becomes substantially homogeneously dispersed in the matrix.
108. A method according to claim 102, wherein the composition is

formed by injecting or extruding alternating substantially transverse layers of

a layer comprising the matrix, the active ingredient optionally being substantially homogeneously dispersed in the matrix, and

- 5 a layer comprising the active ingredient, the active ingredient optionally being substantially homogeneously distributed in matrix material.

109. A method according to claim 108, wherein the alternating layers comprise, respectively, two or more different active substances.

- 10 110. A method for preparing a multiple units pharmaceutical formulation for controlled delivery of an active substance, the method comprising combining in the form of a capsule or tablet a multiplicity of individual units of a composition prepared according to any of claims 88 to 109.

AMENDED CLAIMS

[received by the International Bureau on 18 August 1989 (18.08.89)
original claim 1 amended; new claims 7 and 62 added; all other claims
renumbered wherein claims 31, 54 and 87 are amended; new claims
113 - 170 added (27 pages)]

1. A composition for controlled delivery of an active substance into an aqueous phase by erosion at a substantially constant rate of a surface or surfaces of the composition, the composition comprising

5 a matrix of a substantially water soluble crystalline polymer or a mixture of substantially water soluble crystalline polymers,

a surface active agent or a mixture of surface active agents dispersed in the crystalline polymer phase in an amount of 0-50% by weight of the crystalline polymer and surface active agent, the surface active agent comprising a compound or compounds
10 having at least one domain which is compatible with the crystalline polymer phase and at least one other domain which is substantially lipophilic, and having a melting point which is lower than that of the crystalline polymer,

at least one active substance substantially homogeneously dispersed in the crystalline polymer phase and/or located in geometrically well-defined zones within the composition, and
15

optionally, a filler,

the surface active agent and/or the active substance having a function as a repair medium reducing the water affinity of domains between grains and in cracks in the crystalline polymer matrix and in
20 the crystalline polymer matrix itself, thereby substantially eliminating water diffusion in the interface between the polymer crystals and thus substantially limiting diffusion of water into the composition to the surface layer of the matrix, so that the erosion is predominantly effected by the dissolving action of an aqueous medium on
25 a surface or surfaces of the composition exposed to the medium and takes place at a substantially constant and pH-independent rate, so as to enable a substantially zero order release of the active substance when the active substance is substantially homogeneously
30 distributed in the matrix and the composition has a geometric shape which enables a substantially constant surface area to become exposed during erosion of the matrix.

2. A composition according to claim 1, wherein the crystalline polymer matrix comprises a polyglycol.
3. A composition according to claim 1 or 2, wherein the matrix comprises a homopolymer and/or a copolymer.
- 5 4. A composition according to any of the preceding claims, wherein the matrix comprises a polyethylene glycol and/or a block copolymer of ethylene oxide and propylene oxide.
5. A composition according to claim 4, wherein the block copolymer comprises up to about 30% by weight of the propylene oxide based
10 block, and has a molecular weight of above about 5000 daltons, typically about 5000 to about 30,000 daltons, more typically about 8000 to about 15,000 daltons.
6. A composition according to any of the preceding claims, wherein the crystalline polymer matrix comprises polyethylene glycol with a
15 molecular weight of from about 2000 to about 500,000 daltons, typically from about 5000 to about 100,000 daltons, more typically from about 10,000 to about 50,000 daltons, and especially from about 20,000 to about 35,000 daltons.
7. A composition according to any of claims 1-5, wherein the crystalline
20 line polymer matrix comprises polyethylene glycol with a molecular weight of at least about 20,000 daltons.
8. A composition according to any of the preceding claims, wherein the crystalline polymer matrix has a melting point of about 20-120°C, typically about 30-100°C, more typically about 40-80°C.
- 25 9. A composition according to any of the preceding claims, wherein the active substance is present in an amount of up to about 60%, typically up to about 50%, by weight of the composition.
10. A composition according to any of the preceding claims, which comprises as a filler dextrin, sucralfate, calcium hydroxyl-apatite,
30 calcium phosphate or a fatty acid salt such as magnesium stearate.

11. A composition according to any of the preceding claims, wherein the combination of the filler and the active substance comprises up to about 60%, typically up to about 50%, by weight of the composition.
- 5 12. A composition according to any of the preceding claims, wherein the active substance is a drug for human or veterinary use, a vitamin or other nutritional supplement, a disinfectant, a deodorant or another substance to be administered continuously in an aqueous environment.
- 10 13. A composition according to any of the preceding claims, wherein the active substance is a pharmaceutically active powder.
14. A composition according to claim 13, wherein the powder has a particle size of from about 0.1 μm to about 500 μm , typically from about 0.5 μm to about 300 μm , more typically from about 1 μm to about
15 200 μm , especially from about 5 μm to about 100 μm .
15. A composition according to any of the preceding claims, wherein the surface active agent is a non-ionic emulsifier comprising one or more fatty acid esters and/or fatty acid ethers.
16. A composition according to any of the preceding claims, wherein
20 the surface active agent comprises a fatty acid ester and/or fatty acid ether having carbon chains of from 12 to 24 carbon atoms, typically from 12 to 20 carbon atoms.
17. A composition according to any of the preceding claims, wherein the surface active agent comprises an ester and/or ether of palmitic
25 acid or stearic acid.
18. A composition according to any of the preceding claims, wherein the surface active agent comprises a polyglycol ester or ether such as a polyethylene glycol ester or ether, and/or a sugar ester or ether such as a sorbitan ester or ether.

19. A composition according to any of the preceding claims, wherein the surface active agent comprises a polyethylene glycol monostearate, in particular polyethylene glycol 400 monostearate.
20. A composition according to any of the preceding claims, wherein
5 the surface active agent is present in an amount of about 2-50%, e.g. about 5-50%, typically about 10-40%, more typically about 15-35%, such as about 20-30%, by weight of the crystalline polymer and surface active agent.
21. A composition according to any of the preceding claims which has
10 a geometric shape enabling a substantially constant surface area to become exposed during erosion of the matrix.
22. A composition according to claim 21 which has the shape of a cylindrical rod, and which is provided with a coating which is substantially insoluble in and impermeable to fluids such as body fluids
15 during the intended release period, the coating having an opening at one or both ends.
23. A composition according to claim 22, wherein the coating comprises a matrix of one or more substantially water soluble crystalline polymers and a surface active agent, the coating being one which is
20 eroded in the aqueous phase at a substantially slower rate than the matrix material comprising the active substance, whereby a substantially constant area of the matrix comprising the active substance is exposed during erosion of the composition, and whereby the coating is substantially eroded upon erosion of the matrix comprising
25 the active substance.
24. A composition according to claim 22, wherein the coating is one which disintegrates or crumbles after erosion of the matrix.
25. A composition according to claim 21 which has the shape of a hollow cylinder.
- 30 26. A composition according to claim 21 which has the shape of a hollow hemisphere.

27. A composition according to claim 21 which has the shape of a tablet or slab.

28. A composition according to any of the preceding claims, wherein the active substance is substantially homogeneously dispersed in the
5 crystalline polymer matrix.

29. A composition according to any of the preceding claims, wherein the active substance has at least one domain which is compatible with the crystalline polymer phase and at least one other domain which is substantially lipophilic, the active substance being substantially
10 homogeneously dispersed in the crystalline polymer phase.

30. A composition according to claim 29, wherein the surface active agent is present in the matrix in an amount of about 0-2% by weight of the matrix.

31. A composition according to claim 1, the composition comprising
15 substantially transverse layers comprising

a) a matrix of a substantially water soluble crystalline polymer or a mixture of substantially water soluble crystalline polymers,

20 a surface active agent or a mixture of surface active agents dispersed in the crystalline polymer phase in an amount of 0-50% by weight of the crystalline polymer and surface active agent, the surface active agent comprising a compound or compounds having at least one domain which is compatible with the crystalline polymer phase and at least
25 one other domain which is substantially lipophilic, and having a melting point which is lower than that of the crystalline polymer,

optionally, at least one active substance substantially homogeneously dispersed in the crystalline polymer phase,
30 and

optionally, a filler, and

- b) an active substance, the active substance optionally being substantially homogeneously dispersed in a matrix comprising

5 a substantially water soluble crystalline polymer or a mixture of substantially water soluble crystalline polymers,

10 a surface active agent or a mixture of surface active agents dispersed in the crystalline polymer phase in an amount of 0-50% by weight of the crystalline polymer and surface active agent, the surface active agent comprising a compound or compounds having at least one domain which is compatible with the crystalline polymer phase and at least one other domain which is substantially lipophilic, and having a melting point
15 which is lower than that of the crystalline polymer, and

optionally, a filler,

the composition having the shape of a cylindrical rod and being
20 provided with a coating which is substantially insoluble in and impermeable to fluids such as body fluids during the intended release period, the coating having an opening at one or both ends,

the surface active agent in the matrix of layer a) and in the optional matrix of layer b) having a function as a repair medium reducing the water affinity of domains between grains and in cracks in
25 the crystalline polymer matrix and in the crystalline polymer matrix itself, thereby substantially eliminating water diffusion in the interface between the polymer crystals and thus substantially limiting diffusion of water into the composition to the surface layer of
30 the matrix, so that erosion of the matrix of layer a) and the optional matrix of layer b) is predominantly effected by the dissolving

action of an aqueous medium on a surface or surfaces of the composition exposed to the medium and takes place at a substantially constant and pH-independent rate, so as to enable a substantially zero order release of the active substance when the crystalline polymer matrix of layer a) comprises an active substance substantially homogeneously dispersed therein and/or when the active substance of layer b) is substantially homogeneously dispersed in a crystalline polymer matrix, and so as to enable a strictly controlled pulsatile release of the active substance in layer b) when the active substance in layer b) is not dispersed in a crystalline polymer matrix.

32. A composition according to claim 31, wherein the alternating layers comprise, respectively, two or more different active substances.

33. Use of a composition according to any of the preceding claims in the preparation of a multiple units pharmaceutical formulation, e.g. in the form of a capsule or tablet.

34. A composition for controlled delivery of an active substance into an aqueous phase, the composition comprising

a matrix of room-temperature vulcanizing rubber (RTV rubber) in which particles of a superabsorbent polymer are substantially homogeneously distributed, the superabsorbent polymer particles also being present substantially near the surface of the composition, and

at least one active substance substantially homogeneously dispersed in the matrix and/or located in geometrically well-defined zones within the matrix,

in which the liquid of the aqueous phase is able to diffuse into the matrix at a limited rate, resulting in swelling of the superabsorbent polymer particles and the localized disruption of the matrix in the vicinity of the swollen particles, whereby the active substance is released in a specifically controlled manner according to its distribution in the matrix.

35. A composition according to claim 34, wherein the RTV rubber comprises one or two component RTV silicon elastomers based on polydimethylsiloxane.

36. A composition according to claim 34 or 35, which comprises a catalyst and, optionally, a cross-linking agent.

37. A composition according to any of claims 34-36, wherein the superabsorbent polymer particles are able to remain in a semi-solid state upon absorption of water or other liquids, and are able to absorb at least about 10 times their own weight in water, typically at least about 100 times their own weight in water, especially at least about 200 times their own weight in water.

38. A composition according to any of claims 34-37, wherein the superabsorbent polymer particles are able to remain in a semi-solid state upon absorption of bodily fluids, and are able to absorb at least about 5 times their own weight in bodily fluids, typically at least about 20 times their own weight in bodily fluids, especially at least about 40 times their own weight in bodily fluids.

39. A composition according to any of claims 34-38 wherein the superabsorbent polymer comprises polyacrylic acid, modified polyacrylic acid, carboxymethyl cellulose, modified carboxymethyl cellulose and/or cross-linked polyvinyl pyrrolidone.

40. A composition according to any of claims 34-39 wherein the superabsorbent polymer is present in an amount of about 5-75%, typically about 10-50%, more typically about 20-25% by weight of the matrix.

41. A composition according to any of claims 34-40 wherein the active substance is present in an amount of up to about 60%, typically up to about 50%, by weight of the composition.

42. A composition according to any of claims 34-41 wherein the active substance is a drug for human or veterinary use, a vitamin or other

nutritional supplement, a disinfectant, a deodorant or another substance to be administered continuously in an aqueous environment.

43. A composition according to any of claims 34-42 wherein the active substance is a pharmaceutically active powder.

5 44. A composition according to claim 43, wherein the powder has a particle size of from about 0.1 μm to about 500 μm , typically from about 0.5 μm to about 300 μm , more typically from about 1 μm to about 200 μm , especially from about 5 μm to about 100 μm .

10 45. A composition according to any of claims 34-44 which has a geometric shape enabling a substantially constant surface area to become exposed during erosion of the matrix.

46. A composition according to claim 45 which has the shape of a cylindrical rod, and which is provided with a coating which is substantially insoluble in and impermeable to fluids such as body fluids
15 during the intended release period, the coating having an opening at one or both ends.

47. A composition according to claim 45 which has the shape of a hollow cylinder.

20 48. A composition according to claim 45 which has the shape of a hollow hemisphere.

49. A composition according to claim 45 which has the shape of a tablet or slab.

25 50. A composition according to any of claims 34-49, wherein the active substance is substantially homogeneously dispersed in the matrix.

51. A composition according to claim 46, comprising alternating substantially transverse layers of

a layer comprising the matrix, and optionally comprising the active ingredient substantially homogeneously dispersed in the matrix, and

5 a layer comprising the active ingredient, the active ingredient optionally being substantially homogeneously distributed in matrix material.

52. A composition according to claim 51, wherein the alternating layers comprise, respectively, two or more different active substances.

10 53. Use of a composition according to any of claims 34-52 in the preparation of a multiple units pharmaceutical formulation, e.g. in the form of a capsule or tablet.

15 54. A method for preparing a composition for controlled delivery of an active substance into an aqueous phase by erosion at a substantially constant rate of a surface or surfaces of the composition, the method comprising

combining a substantially water soluble crystalline polymer or a mixture of substantially water soluble crystalline polymers,

20 a surface active agent or a mixture of surface active agents in an amount of 0-50% by weight of the crystalline polymer and surface active agent, the surface active agent comprising a compound or compounds having at least one domain which is compatible with the crystalline polymer phase and at least one other domain which is substantially lipophilic, and having a melting
25 point which is lower than that of the crystalline polymer,

at least one active substance, and

optionally, a filler,

to form a matrix comprising the surface active agent or the mixture of surface active agents dispersed in the crystalline polymer phase

and the active substance substantially homogeneously dispersed in the crystalline polymer phase and/or located in geometrically well-defined zones within the composition, whereby the surface active agent and/or the active substance has a function as a repair medium and reduces the water affinity of domains between grains and in cracks in the crystalline polymer matrix and in the crystalline polymer matrix itself, thereby substantially eliminating water diffusion in the interface between the polymer crystals and thus substantially limiting diffusion of water into the composition to the surface layer of the matrix, so that erosion in an aqueous phase is predominantly effected by the dissolving action of an aqueous medium on a surface or surfaces of the composition exposed to the medium and takes place at a substantially constant and pH-independent rate, so as to enable a substantially zero order release of the active substance when the active substance is substantially homogeneously distributed in the matrix and the composition has a geometric shape which enables a substantially constant surface area to become exposed during erosion of the matrix.

55. A method according to claim 54, wherein the crystalline polymer and the surface active agent are mixed while heating at a temperature sufficient to melt the polymer, and while stirring, so as to obtain a substantially homogeneous mixture, the active substance being added to the molten mixture of the polymer and the surface active agent or added to the mixture prior to heating, whereupon the resulting mixture is shaped and allowed to cool.

56. A method according to claim 54 or 55, wherein the composition is shaped by extrusion, co-extrusion, injection molding or compression molding.

57. A method according to any of claims 54-56, wherein the crystalline polymer comprises a polyglycol.

58. A method according to any of claims 54-57, wherein the crystalline polymer is a homopolymer and/or a copolymer.

59. A method according to any of claims 54-58, wherein the crystalline polymer comprises a polyethylene glycol and/or a block copolymer of ethylene oxide and propylene oxide.
60. A method according to claim 59, wherein the block copolymer
5 comprises up to about 30% by weight of the propylene oxide based block, and has a molecular weight of above about 5000 daltons, typically about 5000 to about 30,000 daltons, more typically about 8000 to about 15,000 daltons.
61. A method according to any of claims 54-60, wherein the
10 crystalline polymer matrix comprises polyethylene glycol with a molecular weight of from about 2000 to about 500,000 daltons, typically from about 5000 to about 100,000 daltons, more typically from about 10,000 to about 50,000 daltons, and especially from about 20,000 to about 35,000 daltons.
- 15 62. A method according to any of claims 54-60, wherein the crystalline polymer matrix comprises polyethylene glycol with a molecular weight of at least about 20,000 daltons.
63. A method according to any of claims 54-62, wherein the
20 crystalline polymer matrix has a melting point of about 20-120°C, typically about 30-100°C, more typically about 40-80°C.
64. A method according to any of claims 54-63, wherein the active substance is added in an amount of up to about 60%, typically up to about 50%, by weight of the composition.
65. A method according to any of claims 54-64, wherein a filler such
25 as dextrin, sucralfate, calcium hydroxyl-apatite, calcium phosphate or a fatty acid salt such as magnesium stearate is added to the mixture of the crystalline polymer and the surface active agent either before or after heating.
66. A method according to any of claims 54-65, wherein the filler
30 and the active substance are added in a combined amount of up to about 60%, typically up to about 50%, by weight of the composition.

67. A method according to any of claims 54-66, wherein the active substance is a drug for human or veterinary use, a vitamin or other nutritional supplement, a disinfectant, a deodorant or another substance to be administered continuously in an aqueous environment.
- 5 68. A method according to any of claims 54-67, wherein the active substance is a pharmaceutically active powder.
69. A method according to claim 68, wherein the powder has a particle size of from about 0.1 μm to about 500 μm , typically from about 0.5 μm to about 300 μm , more typically from about 1 μm to about 10 200 μm , especially from about 5 μm to about 100 μm .
70. A method according to any of claims 54-69, wherein the surface active agent is a non-ionic emulsifier comprising one or more fatty acid esters and/or fatty acid ethers.
71. A method according to any of claims 54-70, wherein the surface 15 active agent comprises a fatty acid ester and/or fatty acid ether having carbon chains of from 12 to 24 carbon atoms, typically from 12 to 20 carbon atoms.
72. A method according to any of claims 54-71, wherein the surface active agent comprises an ester and/or ether of palmitic acid or 20 stearic acid.
73. A method according to any of claims 54-72, wherein the surface active agent comprises a polyglycol ester or ether such as a polyethylene glycol ester or ether, and/or a sugar ester or ether such as a sorbitan ester or ether.
- 25 74. A method according to any of claims 54-73, wherein the surface active agent comprises a polyethylene glycol monostearate, in particular polyethylene glycol 400 monostearate.
75. A method according to any of claims 54-74, wherein the surface active agent is added in an amount of about 2-50%, e.g. about 5-50%,

typically about 10-40%, more typically about 15-35%, such as about 20-30%, by weight of the crystalline polymer and surface active agent.

76. A method according to any of claims 54-75, wherein the composition is formed into a geometric shape enabling a substantially constant surface area to become exposed when the matrix is eroded in an aqueous phase.

77. A method according to claim 76, wherein the composition is formed into the shape of a cylindrical rod and provided with a coating which is substantially insoluble in and impermeable to fluids such as body fluids during the intended release period, the coating having an opening at one or both ends.

78. A method according to claim 77, wherein the composition is formed by co-extrusion of the coating with the matrix and the active substance, or by injection molding, compression molding or extrusion of the matrix and the active substance followed by dip coating or solvent coating by spraying or dipping.

79. A method according to claim 77 or 78, wherein the coating comprises a matrix of one or more substantially water soluble crystalline polymers and a surface active agent, the coating being one which is eroded in the aqueous phase at a substantially slower rate than the matrix material comprising the active substance, whereby a substantially constant area of the matrix comprising the active substance is exposed during erosion of the composition, and whereby the coating is substantially eroded upon erosion of the matrix comprising the active substance.

80. A method according to claim 77 or 78, wherein the coating is one which disintegrates or crumbles after erosion of the matrix.

81. A method according to claim 76, wherein the composition is formed into the shape of a hollow cylinder.

82. A method according to claim 76, wherein the composition is formed into the shape of a hollow hemisphere.

83. A method according to claim 76, wherein the composition is formed into the shape of a tablet or slab.

5 84. A method according to any of claims 54-83, wherein the active substance becomes substantially homogeneously dispersed in the crystalline polymer matrix.

85. A method according to any of claims 54-84, wherein the active substance has at least one domain which is compatible with the
10 crystalline polymer phase and at least one other domain which is substantially lipophilic, the active substance becoming substantially homogeneously dispersed in the crystalline polymer phase.

86. A method according to claim 85, wherein the surface active agent is added to the matrix material in an amount of about 0-2% by weight
15 of the matrix.

87. A method according to claim 54, wherein the composition is formed by injecting or extruding alternating substantially transverse layers comprising

20 a) a substantially water soluble crystalline polymer or a mixture of substantially water soluble crystalline polymers,

a surface active agent or a mixture of surface active agents dispersed in the crystalline polymer phase in an amount of 0-50% by weight of the crystalline polymer and
25 surface active agent, the surface active agent comprising a compound or compounds having at least one domain which is compatible with the crystalline polymer phase and at least one other domain which is substantially lipophilic, and having a melting point which is lower than that of the
30 crystalline polymer,

optionally, at least one active substance substantially
homogeneously dispersed in the crystalline polymer phase,
and

optionally, a filler, and

- 5 b) an active substance, the active substance optionally being
substantially homogeneously dispersed in a mixture
comprising

10 a substantially water soluble crystalline polymer or a
mixture of substantially water soluble crystalline
polymers,

15 a surface active agent or a mixture of surface active
agents dispersed in the crystalline polymer phase in
an amount of 0-50% by weight of the crystalline
polymer and surface active agent, the surface active
agent comprising a compound or compounds having at
least one domain which is compatible with the crystal-
line polymer phase and at least one other domain which
is substantially lipophilic, and having a melting
point which is lower than that of the crystalline
polymer, and

20 optionally, a filler,

25 so as to form a composition having the shape of a cylindrical rod,
the composition being provided with a coating which is substantially
insoluble in and impermeable to fluids such as body fluids during the
intended release period and which has an opening at one or both ends,

30 whereby a crystalline polymer matrix is formed in layer a) and
optionally in layer b), the surface active agent in the matrix of
layer a) and in the optional matrix of layer b) having a function as
a repair medium reducing the water affinity of domains between grains
and in cracks in the crystalline polymer matrix and in the
crystalline polymer matrix itself, thereby substantially eliminating

water diffusion in the interface between the polymer crystals and thus substantially limiting diffusion of water into the composition to the surface layer of the matrix, so that erosion of the matrix of layer a) and the optional matrix of layer b) in an aqueous medium is
5 predominantly effected by the dissolving action of the aqueous medium on a surface or surfaces of the composition exposed to the medium and takes place at a substantially constant and pH-independent rate, so as to enable a substantially zero order release of the active substance when the crystalline polymer matrix of layer a) comprises
10 an active substance substantially homogeneously dispersed therein and/or when the active substance of layer b) is substantially homogeneously dispersed in a crystalline polymer matrix, and so as to enable a strictly controlled pulsatile release of the active substance in layer b) when the active substance in layer b) is not
15 dispersed in a crystalline polymer matrix.

88. A method according to claim 87, wherein the alternating layers comprise, respectively, two or more different active substances.

89. A method for preparing a multiple units pharmaceutical formulation for controlled delivery of an active substance, the
20 method comprising combining in the form of a capsule or tablet a multiplicity of individual units of a composition prepared according to any of claims 54-88.

90. A method for preparing a composition for controlled delivery of an active substance into an aqueous phase, the method comprising
25 combining a room-temperature vulcanizing rubber (RTV rubber) with particles of a superabsorbent polymer and at least one active substance to form a matrix in which the superabsorbent polymer particles are substantially homogeneously distributed and also present substantially near the surface of the composition, and in
30 which the active substance is substantially homogeneously dispersed and/or located in geometrically well-defined zones within the matrix, so that a liquid of an aqueous phase is able to diffuse into the matrix at a limited rate, resulting in swelling of the superabsorbent polymer particles and the localized disruption of the matrix in the
35 vicinity of the swollen particles, whereby the active substance is

released in a specifically controlled manner according to its distribution in the matrix.

91. A method according to claim 90, wherein a catalyst and, optionally, a cross-linking agent is added to the matrix material.

5 92. A method according to claim 90 or 91, wherein the RTV rubber material, the superabsorbent polymer, and the catalytic accelerator and/or cross-linking agent are mixed together at room temperature while stirring, the active substance being added to the mixture before or while stirring, whereupon the mixture is shaped.

10 93. A method according to any of claims 90-92, wherein the composition is shaped by extrusion, co-extrusion, injection molding or compression molding.

94. A method according to any of claims 90-93, wherein the RTV rubber comprises one or two component RTV silicon elastomers based on poly-
15 dimethylsiloxane.

95. A method according to any of claims 90-94, wherein the superabsorbent polymer particles are able to remain in a semi-solid state upon absorption of water or other liquids, and are able to absorb at least about 10 times their own weight in water, typically
20 at least about 100 times their own weight in water, especially at least about 200 times their own weight in water.

96. A method according to any of claims 90-95, wherein the superabsorbent polymer particles are able to remain in a semi-solid state upon absorption of bodily fluids, and are able to absorb at
25 least about 5 times their own weight in bodily fluids, typically at least about 20 times their own weight in bodily fluids, especially at least about 40 times their own weight in bodily fluids.

97. A method according to any of claims 90-96, wherein the superabsorbent polymer comprises polyacrylic acid, modified poly-
30 acrylic acid, carboxymethyl cellulose, modified carboxymethyl cellulose and/or cross-linked polyvinyl pyrrolidone.

98. A method according to any of claims 90-97, wherein the superabsorbent polymer is added in an amount of about 5-75%, typically about 10-50%, more typically about 20-25% by weight of the matrix.

5 99. A method according to any of claims 90-98, wherein the active substance is added in an amount of up to about 60%, typically up to about 50%, by weight of the composition.

10 100. A method according to any of claims 90-99, wherein the active substance is a drug for human or veterinary use, a vitamin or other nutritional supplement, a disinfectant, a deodorant or another substance to be administered continuously in an aqueous environment.

101. A method according to any of claims 90-100, wherein the active substance is a pharmaceutically active powder.

15 102. A method according to claim 101, wherein the powder has a particle size of from about 0.1 μm to about 500 μm , typically from about 0.5 μm to about 300 μm , more typically from about 1 μm to about 200 μm , especially from about 5 μm to about 100 μm .

20 103. A method according to any of claims 90-102, wherein the composition is formed into a geometric shape enabling a substantially constant surface area to become exposed when the matrix is eroded in an aqueous phase.

25 104. A method according to claim 103, wherein the composition is formed into the shape of a cylindrical rod and provided with a coating which is substantially insoluble in and impermeable to fluids such as body fluids during the intended release period, the coating having an opening at one or both ends.

105. A method according to claim 104, wherein the composition is formed by co-extrusion of the coating with the matrix and the active substance, or by injection molding, compression molding or extrusion

of the matrix and the active substance followed by either dip coating or solvent coating by spraying or dipping.

106. A method according to claim 103, wherein the composition is formed into the shape of a hollow cylinder.

5 107. A method according to claim 103, wherein the composition is formed into the shape of a hollow hemisphere.

108. A method according to claim 103, wherein the composition is formed into the shape of a tablet or slab.

109. A method according to any of claims 90-108, wherein the active
10 substance becomes substantially homogeneously dispersed in the matrix.

110. A method according to claim 104, wherein the composition is formed by injecting or extruding alternating substantially transverse layers of

15 a layer comprising the matrix, the active ingredient optionally being substantially homogeneously dispersed in the matrix, and

a layer comprising the active ingredient, the active ingredient optionally being substantially homogeneously distributed in matrix material.

20 111. A method according to claim 110, wherein the alternating layers comprise, respectively, two or more different active substances.

112. A method for preparing a multiple units pharmaceutical formulation for controlled delivery of an active substance, the method comprising combining in the form of a capsule or tablet a
25 multiplicity of individual units of a composition prepared according to any of claims 90-111.

113. A composition according to any of claims 1-32 and 34-52 or a

method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is an antimicrobial agent.

114. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is an antifungal.

115. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is an antiparasitic.

116. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is an antiprotozoal.

117. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is an antiviral agent.

118. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is an antineoplastic agent.

119. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is a cytostatic agent.

120. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is an agent with anticancer properties.

121. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is an analgesic.

122. A composition according to any of claims 1-32 and 34-52 or a

method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is an antiinflammatory agent.

123. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is an anticonvulsant.

124. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is a muscle relaxant.

125. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is a counterirritant.

126. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is a coagulation modifying agent.

127. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is a lipid-regulating agent.

128. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is an anorexic.

129. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is an antacid.

130. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is a gastrointestinal agent.

131. A composition according to any of claims 1-32 and 34-52 or a

method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is an antiemetic.

132. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is a vitamin.

133. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is an electrolyte.

134. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is a micronutrient.

135. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is a macronutrient.

136. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is a purgative.

137. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is a diuretic.

138. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is an antihypertensive agent.

139. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is a β -blocker.

140. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is an antiarrhythmic.

141. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is a cardiac glycoside.

142. A composition according to any of claims 1-32 and 34-52 or a
5 method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is a vasodilator.

143. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is a uricosuric.

10 144. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is a hormone.

145. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim
15 33 or 53, wherein the active substance is an antihormone.

146. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is a contraceptive.

147. A composition according to any of claims 1-32 and 34-52 or a
20 method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is an antidiabetic agent.

148. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is an enzyme.

25 149. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is a vaccine.

150. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is a microorganism.
151. A composition according to any of claims 1-32 and 34-52 or a
5 method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is an antibody.
152. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is a sympathomimetic.
- 10 153. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is an anticholinergic.
154. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim
15 33 or 53, wherein the active substance is a stimulant.
155. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is a central stimulant.
156. A composition according to any of claims 1-32 and 34-52 or a
20 method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is a respiratory stimulant.
157. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is a dopaminergic agent.
- 25 158. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is a para sympathomimetic.
159. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim

33 or 53, wherein the active substance is an ergot or a derivative thereof.

160. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim 5 33 or 53, wherein the active substance is a hypnotic.

161. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is a sedative.

162. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim 10 33 or 53, wherein the active substance is a tranquilizer.

163. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is an antidepressant.

15 164. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is an antiallergic agent.

165. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim 20 33 or 53, wherein the active substance is an antihistamine.

166. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is an expectorant.

167. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim 25 33 or 53, wherein the active substance is a drug antagonist.

168. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is a contrast material.

169. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is a radiopharmaceutical.

5 170. A composition according to any of claims 1-32 and 34-52 or a method according to any of claims 54-112 or a use according to claim 33 or 53, wherein the active substance is a polypeptide.




Fig. 1




Fig. 2




Fig. 3




Fig. 4




Fig. 5




Fig. 6




Fig. 7





Fig. 8

INTERNATIONAL SEARCH REPORT

International Application No PCT/DK89/00068

I. CLASSIFICATION OF SUBJECT MATTER (if several classification symbols apply, indicate all) ⁶		
According to International Patent Classification (IPC) or to both National Classification and IPC ⁴		
A 61 K 47/00, 9/22		
II. FIELDS SEARCHED		
Minimum Documentation Searched ⁷		
Classification System :	Classification Symbols	
IPC ⁴	A 61 K; A 61 L; A 61 M	
Documentation Searched other than Minimum Documentation to the extent that such Documents are included in the Fields Searched ⁸		
SE, NO, DK, FI classes as above		
III. DOCUMENTS CONSIDERED TO BE RELEVANT ⁹		
Category ⁹	Citation of Document, ¹¹ with indication, where appropriate, of the relevant passages ¹²	Relevant to Claim No. ¹³
X	US, A, 4 744 976 (W C SNIPES ET AL) 17 May 1988 See especially column 3, lines 50-60 and column 4, column 8, line 50-column 9, line 2 & WO, 86/00802 AUD, 46388/85 EP, 0190255 US, 4629621 JPT, 61502759 AU, 573149 US, 4774074 CA, 1246448	1-4, 6-11, 14-29, 32 53-57, 60-65, 68-84
X	US, A, 4 629 621 (W C SNIPES ET AL) 16 December 1986 See columns 3, 4 and 7, claims & WO, 86/00802 AUD, 46388/85 EP, 0190255 JPT, 61502759 US, 4744976 AU, 573149 US, 4774074 CA, 1246448 .../...	1-4, 6-11, 14-29, 32, 53-57, 60-65, 68-84
<div style="display: flex; justify-content: space-between;"> <div style="width: 45%;"> <p>¹⁰ Special categories of cited documents:</p> <p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier document but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p> </div> <div style="width: 45%;"> <p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step</p> <p>"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.</p> <p>"A" document member of the same patent family</p> </div> </div>		
IV. CERTIFICATION		
Date of the Actual Completion of the International Search	Date of Mailing of this International Search Report	
1989-06-13	1989-06-13	
International Searching Authority	Signature of Authorized Officer	
Swedish Patent Office	 Niklas Forslund	

III. DOCUMENTS CONSIDERED TO BE RELEVANT (CONTINUED FROM THE SECOND SHEET)

Category *	Citation of Document, with indication, where appropriate, of the relevant passage	Relevant to Claim No.
X	EP, A2, 0 052 916 (ALZA CORPORATION) 2 June 1982 See especially pages 1,2,14 and 17, claims & US, 4346709 US, 4322323	1,2,8-11,14-29, 32,53-57,60-65, 68-84
X	EP, A1, 0 214 735 (EUROCELTIQUE SA) 24 July 1986 See column 4, claims & AUD, 60583/86 FR, 2585246 OA, 8368	1,8-11,14-16, 19,28,29,53
Y	US, A, 4 343 789 (H KAWATA ET AL) 10 August 1982 See the whole document & GB, 2053681 FR, 2460667 DE, 3024858 JP, 56049314 CA, 1146866 SE, 8004938 US, 4404183 CH, 648484 SE, 448342 US, 4673564 JP, 56133217	1-32,53-87
Y	US, A, 4 690 824 (D R POWELL ET AL) 1 September 1987 See especially columns 3-5 & EP, 0131485 AUD, 28898/84 US, 4539198 AU, 561633 CA, 1224417	1-32,53-87
A	US, A, 4 351 825 (G A SOTHMANN ET AL) 28 September 1982 See the whole document	1-32,53-87

FURTHER INFORMATION CONTINUED FROM THE SECOND SHEET

V. ☐ OBSERVATIONS WHERE CERTAIN CLAIMS WERE FOUND UNSEARCHABLE

This international search report has not been established in respect of certain claims under Article 17(2) (a) for the following reasons:

1. ☐ Claim numbers..... because they relate to subject matter not required to be searched by this Authority, namely:

2. ☐ Claim numbers , because they relate to parts of the international application that do not comply with the prescribed requirements to such an extent that no meaningful international search can be carried out, specifically

3. ☐ Claim numbers....., because they are dependent claims and are not drafted in accordance with the second and third sentences of PCT Rule 6.4(a).

VI. ☐ OBSERVATIONS WHERE UNITY OF INVENTION IS LACKING ²

This International Searching Authority found multiple inventions in this international application as follows:

Claim 1-32, 53-87: A controlled delivery composition its use and a method of its preparation comprising a matrix of a substantially water soluble polymer, an active substance dispersed therein and a dispersed surface active agent.

1. ☐ As all required additional search fees were timely paid by the applicant, this international search report covers all searchable claims of the international application.
2. ☒ As only some of the required additional search fees were timely paid by the applicant, this international search report covers only those claims of the international application for which fees were paid, specifically claims:

1-32, 53-87

3. ☐ No required additional search fees were timely paid by the applicant. Consequently, this International search report is restricted to the invention first mentioned in the claims; it is covered by claim numbers.

4. ☐ As all searchable claims could be searched without effort justifying an additional fee, the International Searching Authority did not invite payment of any additional fee.

Remark on Protest

- ☐ The additional search fees were accompanied by applicant's protest.
- ☐ No protest accompanied the payment of additional search fees.

FURTHER INFORMATION CONTINUED FROM THE ~~FIRST SHEET~~ SUPPLEMENTAL SHEET
~~Not for publication~~

Claim 33-52, 88-110: A controlled delivery composition comprising a matrix of RTV-rubber, an active substance and a superabsorbent polymer causing local disrapture in said matrix, its use and a method for its preparation.